									01	LD
RODUCT PRODUIT		PROVINCE OR TERRITORY	PROVINCE O TERRITOIRI				N.T.S. AREA <i>RÉGION DU</i>	S.N.R.C.		REF.
NAME OF PR	OPERTY	L				I			<u>*,</u>	<u></u>
NOM DE LA I		an a				MAP SQL	JARE A7.	No. 91	nc1.1	
	PRODUCT Iron Ore.	· · · · · · · · · · · · · · · · · · ·	FROVINCE Br	ritish	Columbia.			1 12		
	NAME OF PROPERTY Darb	y and Joan.			DEVELOPMENT WOR Series of open-cut		ort adits.		т	
-	NEAREST POST OFFICE	ort Alberni (12 mi.)	).							•
	LOCATION At Smiths Land Mining Division Alberni.	ing. District	BARCLAY							
	County	Township or Parish				•			ł	
	Concession or Range, and Lot							· · ·	Equipped `	
4 17 18	L.S. Sec.	Tp.	<b>R.</b>	_ii		•	· · ·		Not equipped	
-	OWNERS OR OPERATORS A	ND ADDRESS		÷	PRODUCTION					
		· · · · ·							;	
									•	
:					i i i					
4					Material shipped					
1					Date of first shipment	t i				
				е 1	TRANSPORTATION Shipping point					
					Distance from mine		•			
	· · · · · · · · · · · · · · · · · · ·				Carrier	· · ·		· ·		
	DESCRIPTION OF DEPOSIT Ore or substance Magneti	te.			Destination		к <sup>ан</sup>			
					MAP REFERENCES General and district i	maps	•			
	Character of Deposit Repla	cement deposit.		1.1					•	
								• •		
									1	
					Detail maps, plans, se	ections Iron	Ores of Canada I	.G.S. No. 3	3, p. 219.	
	Country Rock	179							. ĝ	
								_	· .	
	Associated minerals of value						121095	5	- - -	
								•		

	BIBLIOGRAPHY	REMARKS					
, ,	B.C. Dept. of Mines Bull. No. 3, 1917, p. 22. The Iron Ores of Canada E.G.S. No. 3, 1926, pp. 218-221.	An approx. average sample from dump: <b>Fe</b> - 55.9% SiO <sub>2</sub> - 16.0 S - 1.0					
		Deposit is too small and grade too low to be of any value as an immediate source of iron.					
1							
1							
	W.R.McG. 10/7/46.						