


BRITISH COLUMBIA
PROSPECTORS ASSISTANCE PROGRAM
MINISTRY OF ENERGY AND MINES
GEOLOGICAL SURVEY BRANCH

PROGRAM YEAR: 1994/95

REPORT #: PAP 94-1

NAME: WALTER GUPPY



WESTRIM 1994 PROGRAM - SIGNIFICANT ASSAYS

Sample No.	Description	Cu ppm	Zn ppm	Ag ppm	Au ppb	Other
94-3	Float - Magnetite w/ chalco.	13343	59	5.5	28	41.35% Fe
94-5	Float - Very large boulder	970	12427	6.1	16	138 ppm pb
94-13	Mineralized shear?	53	57	.5	330	40 ppm As
G94-14	Grab from magnetite showing 10 Meters south of above	1434	300	3.5	12	51% Fe 192Cc
CB 103		573	172	.8	5	32% Fe 182Cc
CB 104	Fossicker Vein	85	68	1.1	5420	
CB 105	" "	61	17	.9	10990	
CB 200		377	225	3.5	920	7462 As
CB 205	Float from NE part of claims	6	11	.1	4	1022 W

35722

18900 (10775) 2078

3099 (1)
31 X 6W

HIGH
GREAT-BEAR
309140
GIANT BEAR
2802 (3)
31 X 5W
(104-134)
501710

5448960

126276
GOLDRIM
216273 3N-4W

STAR 309141
2851 (3)
24X34

STA
309
3N X

104496

LU
302E
25X

BOON
3885
31X3W

AUMONT
3N-2W

WESTERN #5
WESTERN #6
WESTERN #1
WESTERN #2
WESTERN #3
WESTERN #4
WESTERN #7
WESTERN #8
WESTERN #9

Mt. MAITLAND
27303

KING COBRA
3886 (7)
45X3W

1490
1417

ELGER
21X-1E

3094 (3)
3885 (7)

MAP 92F/3W


MIN.
B. C.
NO S

142624

Rocky J.

142624

A COPY OF
Simon Salmon's Field Sketch
Also shows Guppy's
Soil Sampling Baseline
and extra Moss Samples
Base Map From
Kerr Addison 1987 Report Scale: 5000



300N

0

50E

100E

150E

200E

250E

300E

250N

200N

150N

100N

50N

50S

100S

150S


200S

250S

300S

350S

74
 74
 56
 56
 119
 34



WESTRIM M.C.
 1994 Soil Sampling
 Sample Location $\frac{CV}{ZN}$ PAU
 Scale 1cm = 25M

61
237 017

37 012
34 029

30
128 02

14 02
58

23 09
28

22 08
26

34 032
35

DCP

CREEK

OLD SLIDE
 No Suitable Soil

BOULDERS
 AND TALUS

N.S.S.

N.S.S.

84 04
29

17 02
19

55 014
23

51 06
15

65 015
38

74 03
509

77 04
35

19 024
24

49 014
351

Flowing

SLIDE

63 04
33

19 047
18

53 026
27

4 063
12

11 04
25

VEIN

N.S.S.

12 023
28

32 029
25

5 017
12

18 055
10

12 063
18

55 054
23

Manahy

014

014

014

014

014

014


014

014

ROCK


ROAD

ROAD



03


01



AUMONT
L.C.P. TRUE POSITION

L. 1491 C.S.

G.R. 150



AUMONT MOUNTAIN

WESTRIM #8

AUMONT W.P.

#2 Post

WESTRIM #7

#1 Posts

WESTRIM #1

#2 Post
WESTRIM
land 2

#1 Post
WESTRIM
5a and b

WESTRIM #5

#2 Post
W.P.

WESTRIM #7

#1 Post

WESTRIM #3

WESTRIM #2

W.P. GOLDRIM
L.C.R. 450M 0°

WESTRIM #6

WESTRIM GROUP
CLAIM LINES AND
TOPOGRAPHY
Scale 1:5000

GOLDRIM 3N-4W



GEOCHEMICAL ANALYSIS CERTIFICATE



Walter Guppy File # 94-2417 Page 1

Box 94, Tofino BC V0R 2Z0

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
94-1	1	10	2	86	<.1	13	14	814	4.60	3	<5	<2	<2	37	<.2	<2	5	61	.76	.113	6	3	1.88	4	.24	2	1.98	.02	.02	1	3
94-2	<1	3	12	120	<.1	1	18	576	44.60	6	45	<2	7	4	1.3	7	23	<2	.74	.003	<2	<1	.12	5	<.01	<2	.11	.01	<.01	<1	2
94-3	<1	13343	10	59	5.5	128	86	95	41.35	<2	50	<2	8	18	2.5	13	37	39	.24	<.001	<2	15	.20	5	.08	<2	.33	.01	<.01	2	28
94-4	8	80	<2	413	.2	54	33	408	5.18	20	<5	<2	<2	99	<.2	<2	2	104	3.76	.112	<2	47	7.06	42	.21	21	6.91	.07	.09	<1	8
94-5	<1	970	138	12427	6.1	1	40	3056	10.25	3	<5	<2	<2	5	57.5	<2	18	4	1.92	.002	<2	3	.11	13	<.01	<2	.16	<.01	.01	<1	16
94-6	1	241	7	3910	.3	7	34	1835	30.06	2	12	<2	6	4	20.0	<2	9	5	3.20	.004	<2	2	.10	6	<.01	<2	.10	.01	<.01	<1	21
94-7	<1	20	6	38	.1	2	2	766	.71	4	8	<2	3	115	<.2	3	<2	6	8.35	.005	3	4	.18	9	.01	3	.29	<.01	.04	4	2
94-8	1	15	4	145	.3	6	8	1188	1.73	<2	<5	<2	5	114	.5	<2	<2	17	13.64	.018	3	7	.51	18	.03	3	.73	<.01	.08	2	3
94-9	<1	599	18	9942	.6	1	39	740	27.93	<2	10	<2	5	8	55.6	2	14	6	.32	.003	<2	<1	.22	4	<.01	<2	.35	.01	<.01	<1	18
94-10	<1	124	11	61	.3	36	20	85	33.20	10	26	<2	6	33	3.1	6	10	31	.40	.008	<2	43	.15	5	.05	<2	.37	.01	.01	12	9
94-11	<1	4473	28	490	2.7	22	79	3965	11.89	42	14	<2	7	2	2.1	<2	15	28	9.71	<.001	<2	6	2.77	2	<.01	<2	.97	<.01	<.01	9	13
94-12	2	203	7	377	.7	8	13	1835	4.47	38	6	<2	4	101	1.4	<2	2	25	9.96	.009	3	8	1.51	4	<.01	<2	1.24	<.01	.02	<1	140
94-13	1	53	12	57	.5	5	8	1034	3.38	40	<5	<2	<2	34	.2	<2	<2	18	3.76	.009	<2	7	.42	5	<.01	2	.7	.01	.04	4	330
CS-1	3	73	4	46	.3	10	8	348	3.23	3	<5	<2	<2	4	<.2	3	<2	18	1.16	.006	<2	10	.25	12	<.01	<2	.69	.01	.05	3	120
RE CS-1	3	72	3	45	.2	10	7	352	3.15	3	<5	<2	<2	4	<.2	3	2	17	.15	.006	<2	10	.24	12	<.01	2	.67	.01	.05	3	170
CS-2	2	23	<2	113	.1	6	25	1135	6.41	2	<5	<2	<2	44	<.2	<2	5	119	2.73	.072	5	8	3.50	15	.17	<2	3.99	.03	.06	<1	13
75E-225S	2	44	13	89	<.1	25	34	796	6.16	6	<5	<2	<2	55	<.2	<2	5	62	1.14	.070	<2	12	1.14	24	.19	4	2.65	.12	.14	2	8
90E-150S	2	274	5	192	.1	16	21	2007	6.61	4	<5	<2	2	29	.2	<2	5	124	1.40	.092	<2	19	2.88	23	.17	<2	5.19	.06	.05	<1	8
101E-150S	1	207	7	108	<.1	9	21	1400	8.54	<2	<5	<2	3	19	<.2	<2	6	162	.25	.103	2	12	1.76	24	.30	<2	2.51	.04	.09	<1	23
350S	1	75	2	150	<.1	11	17	1119	4.54	2	<5	<2	<2	62	.3	<2	9	75	1.05	.141	3	12	1.71	101	.19	3	2.42	.05	.10	<1	4
STANDARD C/AU-R	20	57	41	123	6.6	75	31	1037	3.96	41	13	6	35	49	16.6	15	22	60	.51	.090	41	55	.89	182	.08	33	1.88	.06	.16	12	490

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.
 ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
 - SAMPLE TYPE: P1 ROCK P2 TO P3 SOIL P4 MOSS MAT AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.
 Samples beginning 'RE' are duplicate samples.

DATE RECEIVED: AUG 5 1994 DATE REPORT MAILED: Aug 11/94 SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS



AA ANALYTICAL



AA ANALYTICAL

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
00-25N	2	34	13	35	<.1	11	8	153	6.27	5	<5	<2	3	16	.2	4	7	197	.32	.021	2	34	.26	15	.24	3	2.65	.01	.02	2	32
SON	1	22	12	36	<.1	7	9	128	5.08	2	<5	<2	<2	13	<.2	4	<2	159	.25	.020	3	19	.16	14	.19	2	1.37	.01	.04	<1	8
75N	4	23	13	28	<.1	3	3	<2	8.40	.4	<5	<2	3	8	.2	2	2	242	.09	.024	<2	23	.08	17	.19	<2	4.47	.01	.04	9	9
100N	2	14	14	58	<.1	4	10	2333	3.58	<2	<5	<2	<2	19	.3	<2	<2	109	.47	.021	2	9	.30	39	.05	<2	1.94	.01	.07	<1	2
125N	3	30	14	228	<.1	7	7	178	6.49	113	9	<2	2	16	.6	<2	2	140	.78	.019	4	26	.19	23	.31	2	3.15	.01	.04	<1	2
RE 150N +10	7	37	8	34	<.1	6	6	80	8.51	11	<5	<2	3	9	.3	2	<2	212	.17	.020	2	39	.18	10	.19	<2	3.75	.01	.02	2	12
150N +10	6	38	9	34	<.1	7	6	80	8.58	6	<5	<2	3	9	.4	2	2	214	.18	.020	3	39	.18	10	.19	<2	3.76	.01	.02	<1	29
175N	5	61	4	237	.1	21	15	366	6.80	25	11	<2	2	16	.6	<2	2	146	.69	.022	3	45	.90	20	.27	2	6.23	.01	.01	<1	7
X-100	5	52	2	141	.3	34	360	47620	20.03	253	<5	<2	<2	17	4.3	<2	<2	129	.65	.074	8	77	.05	201	.06	8	4.62	<.01	.01	<1	7
100S	7	84	<2	29	<.1	9	11	173	7.33	28	<5	<2	3	8	<.2	<2	<2	138	.07	.056	4	17	.38	39	.14	<2	7.12	.01	.02	<1	4
125S	1	17	6	19	<.1	4	7	117	5.43	3	<5	<2	2	14	<.2	4	2	162	.13	.029	2	9	.20	13	.21	2	1.51	.01	.03	1	2
150S	5	55	<2	23	<.1	6	9	540	7.38	5	<5	<2	2	10	.3	<2	3	112	.18	.093	4	17	.26	27	.19	<2	7.41	.01	.03	<1	3
175S	3	51	2	15	<.1	6	7	127	7.36	<2	<5	<2	3	9	.2	4	<2	149	.11	.041	4	25	.23	18	.12	<2	4.06	.01	.02	<1	6
250S A	1	74	18	509	.5	17	11	2667	2.32	13	<5	<2	<2	51	1.8	<2	<2	44	3.27	.110	10	87	.95	67	.05	16	3.21	.02	.04	2	14
250S B	3	21	11	22	<.1	5	9	74	6.26	5	<5	<2	2	12	.2	3	6	226	.13	.024	2	22	.15	17	.16	<2	2.16	.01	.02	<1	2
275S	1	77	6	35	<.1	20	9	220	5.28	<2	<5	<2	2	21	<.2	3	2	163	.29	.025	<2	53	.81	10	.51	2	4.66	.01	.01	7	4
300S	3	47	14	351	<.1	10	13	537	6.15	46	15	<2	2	22	.5	<2	<2	195	.79	.033	5	110	.43	24	.31	3	5.16	.01	.02	1	14
50E-250N	1	119	4	34	.1	15	8	149	6.43	6	<5	<2	3	16	<.2	4	<2	202	.34	.038	<2	51	.62	10	.42	2	4.57	.01	.02	8	2
50E-275N	2	56	5	56	<.1	14	12	629	5.40	3	<5	<2	2	16	.2	<2	3	144	.37	.049	2	46	.45	19	.32	3	4.17	.01	.04	<1	3
50E-300N	1	34	6	34	<.1	10	5	60	8.62	4	<5	<2	3	16	<.2	<2	2	225	.24	.025	<2	58	.27	10	.49	<2	3.13	.01	.02	<1	3
50E-325N	2	27	6	14	.2	5	3	<2	10.54	3	<5	<2	3	10	<.2	<2	2	444	.13	.017	<2	63	.11	5	.74	<2	2.22	.01	.02	<1	6
50E-350N	2	13	7	14	<.1	4	3	9	5.77	<2	<5	<2	2	11	<.2	5	6	246	.13	.016	2	25	.06	9	.37	2	1.41	.01	.03		
50E-375N	7	7	5	22	<.1	4	2	38	6.33	6	<5	<2	3	16	<.2	<2	3	251	.19	.014	<2	33	.16	10	.45	<2	1.99	.01	.04		
50E-400N	2	26	10	33	.3	8	5	100	8.64	4	<5	<2	3	14	<.2	5	<2	219	.20	.020	<2	62	.27	10	.56	2	2.39	.01	.03		
100E-150S	2	63	2	33	<.1	11	6	160	7.14	2	<5	<2	3	14	<.2	<2	2	185	.18	.032	<2	47	.30	11	.51	2	4.56	.01	.03	3	4
100E-200S	2	19	2	18	<.1	6	3	<2	9.20	2	<5	<2	3	12	<.2	2	2	229	.16	.023	<2	54	.15	10	.46	<2	2.54	.01	.02	<1	47
100E-225S	1	55	9	27	<.1	13	7	105	7.81	5	<5	<2	3	14	.2	3	3	248	.21	.021	<2	63	.38	8	.53	2	3.49	.01	.01	<1	26
100E-275S	1	4	8	12	<.1	3	2	38	3.85	3	<5	<2	2	14	<.2	5	3	228	.25	.012	<2	20	.06	6	.46	<2	.89	.01	.03	<1	62
100E-300S	1	11	5	25	<.1	5	4	62	5.56	3	<5	<2	2	16	<.2	4	5	196	.21	.024	<2	24	.11	10	.38	<2	1.35	.01	.03	<1	4
125E-225S	1	18	4	19	<.1	6	3	6	7.52	<2	<5	<2	3	10	<.2	2	2	226	.14	.034	<2	49	.14	9	.37	2	3.35	.01	.04	<1	5
125E-225S D	1	14	7	16	<.1	5	4	<2	7.61	7	<5	<2	2	10	<.2	3	3	254	.12	.026	<2	43	.10	9	.37	<2	2.29	.01	.02	<1	4
125E-275S	1	13	2	19	.2	3	1	37	3.15	2	<5	<2	<2	19	<.2	4	5	225	.22	.017	<2	25	.09	6	.55	2	1.42	.01	.03	<1	4
125E-300S	1	55	2	23	.1	10	4	61	6.05	<2	<5	<2	3	10	<.2	<2	2	166	.16	.037	3	79	.26	6	.39	2	8.17	.01	.01	<1	4
200E-125S	1	12	11	28	.1	5	4	91	5.95	4	<5	<2	2	13	<.2	4	4	216	.22	.022	<2	31	.08	8	.34	<2	1.13	.01	.03	<1	23
200E-175S	3	32	5	25	.1	7	4	49	6.76	3	<5	<2	3	14	<.2	4	5	222	.17	.016	<2	72	.17	10	.43	2	4.90	.01	.02	3	3
STANDARD C/AU-S	19	58	38	122	6.8	74	31	1003	3.96	40	21	6	36	49	16.7	16	22	60	.50	.090	41	56	.85	181	.08	33	1.88	.06	.15	11	47

Sample type: SOIL. Samples beginning 'RE' are duplicate samples.

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
200E-175S D	<1	43	17	20	<.1	8	<1	196	9.40	<2	13	<2	<2	10	<.2	3	<2	230	.17	.031	2	81	.22	8	.59	<2	5.29	.01	.02	<1	7
200E-200S	<1	5	2	14	.2	2	1	105	.59	5	5	<2	<2	4	<.2	2	<2	27	.09	.009	2	4	.04	9	.05	5	.63	.01	.03	<1	17
225E-150S	2	13	21	37	.1	5	5	196	8.38	<2	10	<2	<2	11	<.2	<2	<2	164	.15	.024	3	21	.14	10	.32	3	1.27	.01	.03	1	14
250E-150S	<1	67	20	75	.2	20	17	653	7.91	17	7	<2	<2	19	<.2	<2	<2	97	.91	.022	2	32	1.12	14	.20	4	2.30	.02	.02	<1	470
250E-175S	4	47	11	32	.1	12	4	293	7.39	<2	14	<2	2	9	<.2	3	<2	180	.18	.028	<2	69	.54	8	.46	<2	6.80	.01	.02	1	12
200S-25W	5	65	18	38	.6	5	7	300	6.12	<2	<5	<2	<2	7	<.2	3	<2	108	.09	.050	3	23	.26	16	.10	<2	5.72	.01	.02	<1	15
300S-25W	1	19	17	24	.3	5	9	416	6.81	<2	<5	<2	<2	10	<.2	2	2	152	.12	.055	2	20	.29	21	.07	<2	3.15	.01	.03	2	24
50E 150S SILT	<1	77	18	331	<.1	16	20	1512	6.34	10	<5	<2	<2	25	.4	<2	<2	111	1.32	.056	4	42	.99	28	.22	<2	2.83	.03	.03	<1	53
STANDARD C/AU-S	19	57	40	126	7.2	71	33	1069	4.22	42	20	8	36	52	18.3	14	19	61	.51	.096	40	58	.92	185	.07	34	2.03	.06	.14	13	48

Sample type: SOIL.



ACHE ANALYTICAL



ACHE ANALYTICAL

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
94-M-1	1	137	28	121	.3	38	26	1063	5.65	<2	<5	<2	<2	35	1.0	<2	<2	101	.85	.068	4	39	1.49	38	.17	7	2.30	.02	.05	1	46
94-M-2	1	162	25	118	.4	38	29	990	7.69	<2	<5	<2	<2	38	.8	<2	<2	104	.91	.056	5	55	1.52	23	.19	7	2.22	.03	.06	3	9
94-M-3	<1	147	13	43	.3	67	23	656	5.20	3	<5	<2	<2	53	.5	<2	<2	113	1.03	.046	3	81	1.65	8	.39	3	2.19	.02	.05	2	3
RE 94-M-5	<1	118	19	71	.3	50	29	1108	3.55	10	5	<2	<2	28	.4	4	<2	97	1.00	.054	3	48	1.10	13	.24	7	2.60	.02	.03	<1	12
94-M-4	1	41	14	36	<.1	15	13	639	3.69	6	<5	<2	<2	19	.3	<2	<2	52	.47	.071	2	13	.66	18	.05	<2	1.36	.02	.11	<1	4
94-M-5	1	117	18	66	<.1	47	27	1079	3.46	9	<5	<2	<2	27	.3	<2	<2	90	.97	.051	2	51	1.05	12	.23	3	2.57	.03	.03	<1	8
94-M-6	1	163	17	73	<.1	53	44	1679	2.78	3	<5	<2	<2	37	.4	<2	<2	61	1.57	.080	5	59	.70	32	.10	4	4.06	.02	.06	<1	3
94-M-7	<1	202	32	590	.6	33	72	3779	10.38	182	<5	<2	<2	23	2.3	<2	<2	59	1.46	.062	4	20	1.12	40	.09	6	3.20	.01	.04	<1	1060
94-M-8	<1	36	20	32	<.1	10	5	272	1.68	<2	<5	<2	<2	15	.2	<2	<2	74	.27	.056	2	11	.18	12	.16	2	1.21	.03	.19	1	6
94-M-9	1	142	47	28	.2	25	11	400	2.30	<2	<5	<2	<2	18	<.2	2	<2	59	.41	.073	3	24	.48	11	.10	3	2.06	.02	.08	3	6
94-M-10	<1	93	47	72	.3	28	13	569	3.43	7	<5	<2	<2	23	.7	2	<2	82	.51	.056	3	24	.86	13	.18	6	2.23	.02	.10	1	380
94-M-11	<1	116	12	65	.2	49	27	693	5.51	7	<5	<2	<2	46	<.2	<2	<2	113	1.05	.045	3	60	1.59	11	.35	2	2.19	.01	.03	<1	16
94-M-12	<1	83	14	70	.2	53	28	1161	6.16	16	<5	<2	<2	30	<.2	<2	<2	110	.69	.057	4	65	1.80	29	.13	6	2.68	.01	.05	1	120
GRN 00	<1	118	15	30	.1	47	25	787	5.46	4	<5	<2	<2	17	<.2	<2	<2	116	1.12	.049	3	49	1.62	12	.33	3	2.34	.01	.02	<1	13
GRN 1R	1	56	14	343	.3	17	22	1617	3.01	4	<5	<2	<2	23	.2	<2	<2	75	.73	.047	4	23	.60	28	.18	2	2.90	.02	.05	<1	110
X-350	<1	23	11	131	.1	9	10	1308	2.04	5	<5	<2	<2	36	2.2	<2	<2	58	1.82	.070	5	28	.31	37	.08	11	2.87	.03	.14	<1	3
50E-280N	2	46	14	58	.2	22	33	2773	2.73	10	5	<2	<2	48	.2	2	<2	72	1.11	.073	3	22	.68	39	.18	9	1.82	.04	.15	2	11
275S-25W	<1	32	14	254	.5	10	8	1371	1.43	<2	7	<2	<2	34	1.4	2	<2	29	2.21	.091	5	14	.95	31	.03	62	1.26	.04	.22	2	11
STANDARD C/AU-S	19	57	40	126	7.2	71	33	1069	4.22	42	20	8	36	52	18.3	14	19	61	.51	.096	40	58	.92	185	.07	34	2.03	.06	.14	13	45

Sample type: MOSS MAT. Samples beginning 'RE' are duplicate samples.

GEOCHEMICAL ANALYSIS CERTIFICATE

Walter Guppy File # 94-3071 Page 1

Box 94, Tofino BC V0R 2Z0



SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
G-94-14	<1	1434	4	300	3.5	5	192	1551	51.17	5	<5	<2	8	3	8.3	5	<2	18	3.08	.006	<2	1	.11	10	<.01	38	.23	.03	.03	<1	12
G-94-15	3	13300	23	25	52.9	16	4	119	4.12	5	<5	<2	<2	1	1.8	<2	14	32	.05	<.001	<2	24	.35	<2	.04	5	.50	.01	.03	<1	48
G-94-16	20	512	8	5046	1.7	8	43	6030	24.82	23	<5	<2	6	3	32.3	<2	<2	11	2.35	<.001	<2	2	.06	13	<.01	16	.14	<.01	.02	<1	19
G-94-17	6	199	<2	59	.4	13	27	455	5.62	10	<5	<2	<2	86	.7	<2	<2	63	2.54	.062	2	8	1.25	26	.10	<2	6.37	.15	.08	<1	20
G-94-17B	21	151	6	157	.3	20	21	766	8.11	65	<5	<2	2	126	1.2	<2	4	141	3.28	.154	4	9	1.99	24	.07	<2	6.65	.18	.02	<1	15
RE G-94-17B	20	148	<2	156	.2	23	23	761	8.04	66	<5	<2	<2	125	.9	<2	3	141	3.25	.150	4	9	1.95	28	.07	4	6.49	.18	.02	<1	14
BSE-94-1	5	83	20	18	1.0	43	37	146	12.53	257	<5	<2	2	5	.4	2	<2	9	.09	.004	<2	19	.22	5	.02	14	.47	.02	.14	<1	330

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.
 ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
 - SAMPLE TYPE: P1 ROCK P2 SOIL P3 MOSS MAT AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.
 Samples beginning 'RE' are duplicate samples.

DATE RECEIVED: SEP 8 1994 DATE REPORT MAILED: *Sept 16/94* SIGNED BY: *C. Leong* .D.TOYE, C.LEONG, J.WANG; CERTIFIED B.C. ASSAYERS



SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
A10N	2	34	17	62	<.1	5	3	231	1.54	<2	<5	<2	<2	13	<.2	<2	<2	53	.46	.034	3	14	.40	20	.12	2	1.78	.02	.04	1	14
A10NW	2	74	10	135	<.1	22	12	525	3.42	7	<5	<2	<2	27	.5	2	<2	78	1.18	.063	3	30	1.11	26	.17	5	2.54	.02	.04	1	64
A10NE	2	3	6	14	<.1	1	<1	58	1.36	<2	<5	<2	<2	5	<.2	<2	<2	111	.06	.007	3	3	.03	8	.15	3	.41	.01	.02	1	12
A10W	1	3	7	29	<.1	1	1	48	.99	<2	<5	<2	<2	9	<.2	2	2	40	.11	.013	5	2	.04	19	.07	3	.39	.01	.05	1	2
A10S	2	26	11	61	.3	8	7	375	4.26	<2	<5	<2	<2	18	<.2	2	2	113	.53	.032	2	18	.50	12	.17	2	1.23	.01	.04	1	12
RE A10S	2	25	10	59	.2	9	7	364	4.12	3	<5	<2	<2	18	.4	3	<2	109	.50	.031	3	18	.48	11	.16	3	1.19	.01	.04	1	12
STANDARD C/AU-S	19	58	38	134	7.1	72	32	1023	4.09	39	16	7	36	51	18.0	15	20	61	.50	.093	40	58	.92	189	.08	33	1.99	.07	.16	13	48

Sample type: SOIL. Samples beginning 'RE' are duplicate samples.



SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
94M13	1	29	10	31	<.1	12	13	515	3.94	<2	<5	<2	<2	23	<.2	3	<2	107	.45	.043	2	23	.48	19	.19	4	1.77	.01	.06	1	3
94M14	1	44	8	51	<.1	33	38	1521	3.26	11	<5	<2	<2	34	<.2	<2	<2	94	.76	.030	2	35	.89	19	.25	5	1.92	.03	.06	<1	3
94M15	1	219	14	121	.4	33	32	1172	4.89	<2	<5	<2	<2	48	.8	3	<2	102	1.27	.092	5	45	1.51	22	.17	7	2.58	.02	.10	1	67
94M16	<1	116	8	83	.2	38	29	640	6.61	<2	<5	<2	<2	51	.8	<2	<2	140	1.23	.048	3	46	1.55	15	.32	3	2.18	.02	.03	<1	780
RE 94M16	<1	110	5	78	.1	35	29	620	6.62	<2	<5	<2	<2	49	.5	<2	<2	136	1.17	.046	2	45	1.45	14	.31	<2	2.02	.02	.03	<1	5830

Sample type: MOSS MAT. Samples beginning 'RE' are duplicate samples.

GEOCHEMICAL ANALYSIS CERTIFICATE

Walter Guppy File # 94-3357

Box 94, Tofino BC V0R 2Z0



SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
94-G17M	1	118	10	62	.1	32	24	585	5.26	13	<5	<2	<2	49	<.2	<2	<2	111	.96	.041	3	60	1.46	8	.38	2	1.93	.01	.03	<1	5
94-G18M	<1	62	12	70	<.1	15	18	1423	3.92	14	<5	<2	<2	34	.5	<2	<2	69	1.02	.076	6	21	1.01	49	.10	2	2.24	.01	.05	<1	4
94-G19M	1	33	16	25	.1	6	29	2463	1.97	3	<5	<2	<2	16	.3	<2	<2	44	.21	.109	5	7	.21	37	.06	4	2.41	.01	.07	1	83
94-G20M	<1	113	7	78	.3	31	22	620	5.30	11	<5	<2	<2	47	<.2	<2	<2	117	1.01	.043	3	61	1.58	10	.38	<2	2.10	.02	.03	<1	13

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.
 - SAMPLE TYPE: MOSS MAT AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.

DATE RECEIVED: SEP 27 1994

DATE REPORT MAILED: Oct 4/94

SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS



GEOCHEMICAL ANALYSIS CERTIFICATE



Walter Guppy File # 94-3823
 Box 94, Tofino BC V0R 2Z0 Submitted by: Chris Baldys

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	%	%	%	%	ppm	ppb
100	1	101	8	12574	.8	12	80	5461	10.63	75	<5	<2	10	26	68.5	<2	<2	12	11.14	.003	<2	3	.68	10	.01	4	.34	<.01	.01	<1	20
101	1	110	9	197	.4	9	14	2332	4.05	26	<5	<2	9	147	1.6	<2	<2	32	17.60	.013	2	6	1.76	8	<.01	4	1.48	.01	.01	<1	120
102	3	144	4	74	.6	15	10	1774	4.01	34	<5	<2	7	112	.6	<2	3	35	8.57	.012	2	10	1.76	8	<.01	7	1.49	.01	.01	<1	430
103	<1	573	2	172	.8	20	182	2417	32.13	2	13	<2	9	5	1.1	<2	3	16	6.09	.006	<2	3	.26	13	<.01	<2	.30	.02	.02	2	5
104	4	85	12	68	1.1	19	24	1359	5.77	22	<5	5	3	6	.3	<2	<2	31	.18	.055	5	19	.75	42	.01	7	1.57	.02	.13	215	5420
105	1	61	17	17	.9	6	3	242	4.51	18	<5	<2	<2	4	<.2	<2	4	2	.38	.002	<2	5	.03	10	<.01	<2	.08	.01	.02	36	10990
106	<1	13	4	98	.1	19	26	887	7.00	8	<5	<2	3	20	.2	<2	<2	48	.71	.166	3	8	1.94	37	.09	<2	2.77	.05	.12	2	8
107	<1	23	<2	55	<.1	18	19	1059	6.11	3	<5	<2	2	21	.2	2	<2	56	.41	.101	2	7	1.65	61	.15	<2	2.75	.05	.20	1	10
108	3	24	2	48	<.1	12	18	640	5.64	3	<5	<2	3	17	<.2	<2	<2	42	.11	.027	2	3	1.04	28	.03	2	1.74	.06	.08	3	6
109	1	41	2	94	.1	12	13	1471	6.87	<2	<5	<2	2	32	<.2	<2	<2	76	.34	.060	3	5	1.78	50	.01	<2	3.56	.09	.09	1	2
110	5	29	4	44	.1	3	3	546	6.72	7	<5	<2	3	22	<.2	<2	<2	27	.09	.046	2	4	.98	50	.03	5	1.70	.07	.10	2	2
RE 110	4	29	5	43	<.1	6	3	532	6.66	6	<5	<2	2	21	<.2	2	<2	26	.09	.045	2	4	.97	47	.03	2	1.67	.07	.10	<1	2
111	13	28	5	39	<.1	4	10	548	7.75	17	<5	<2	3	31	<.2	<2	<2	31	.33	.086	2	2	1.23	39	.04	2	1.88	.09	.08	7	9
112	5	19	7	10	.2	4	25	106	3.85	7	<5	<2	4	7	.2	4	<2	25	.25	.079	2	6	.35	44	.20	3	.72	.03	.21	2	8
200	3	377	82	225	3.5	16	10	1826	5.93	7462	<5	<2	9	87	2.0	92	<2	25	10.36	.017	3	6	4.08	15	<.01	3	.83	.01	.07	<1	920
201	<1	670	<2	280	.9	17	162	2347	28.89	133	17	<2	9	58	.4	<2	<2	46	7.67	.016	2	5	2.38	17	.01	4	1.60	.02	.05	<1	63
202	<1	53	3	182	.1	8	28	3454	10.48	23	5	<2	6	3	.5	<2	<2	9	6.96	.004	<2	1	.27	9	<.01	8	.22	.01	.01	9	6
203	2	24	4	66	<.1	27	42	696	9.12	55	<5	<2	2	120	<.2	<2	<2	102	2.30	.195	2	10	1.13	50	.08	<2	2.80	.21	.15	<1	10
205	1	6	2	11	<.1	6	2	2776	.85	4	<5	<2	12	272	<.2	<2	3	7	37.48	.015	13	1	.24	15	<.01	4	.21	.01	.04	1022	4
206	1	8	<2	45	<.1	5	11	851	2.70	2	<5	<2	<2	3	<.2	<2	<2	43	.33	.015	<2	6	.96	14	<.01	<2	1.37	<.01	.04	8	5
STANDARD C/AU-R	19	60	41	128	7.0	72	32	1045	3.96	42	17	7	37	52	18.6	14	21	62	.50	.094	41	61	.90	185	.09	33	1.88	.06	.15	13	510

metallurgical assay requested to follow

metallurgical to follow

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.
 ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS > 1%, AG > 30 PPM & AU > 1000 PPB
 - SAMPLE TYPE: ROCK AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE. Samples beginning 'RE' are duplicate samples.

DATE RECEIVED: OCT 21 1994 DATE REPORT MAILED: *Oct 25/94* SIGNED BY: *[Signature]* .D.TOYE, C.LEONG, J.WANG; CERTIFIED B.C. ASSAYERS