


**BRITISH COLUMBIA**  
**PROSPECTORS ASSISTANCE PROGRAM**  
**MINISTRY OF ENERGY AND MINES**  
**GEOLOGICAL SURVEY BRANCH**

PROGRAM YEAR: 1994/95

REPORT #: PAP 94-29

NAME: SIMON SALMON

Program Completion  
On the Auric Claim  
Warn Bay, Fortune Channel  
Western Vancouver island, B.C.  
Alberni Mining Division  
NTS 92F/5E  
S.Salmon Prospector 10/12/94



## INDEX

	Page
Auric work program:	
Improve access:	1
Map area geology:	1
Reopen and sample workings:	2
Soil samples:	3
Moss mat samples:	4
Prospecting:	5
Auric assays:	6
Workings maps:	11
Moss mats results:	15
Conclusions:	19
Overlord work program:	20
Overlord samples:	22
Workings map Overlord claim:	24
Conclusions:	25
Diary:	26
Budget:	27
Completion forms:	28
Notices of work:	30
Assays:	33

## AURIC WORK PROGRAM

### Improve Access:

The proposed route to the Free Gold claim was not feasible. This new route was hiked twice at different elevations. This new route crossed three steep slides and ended in a canyon on the creek north of the workings. Another route was attempted up Free Gold Creek, but this route also proved to be steep and dangerous.

So once again the old timers found the best route. The original trail is steep, but is the only way in for the time being. The old trail was brushed out and the windfalls were removed by chainsaw. This was a big improvement. The trail was also reflagged and blazed.

Two separate trails lead from the old camp to the workings. These were also brushed out and cleared, although one bridge and two lengths of rope were needed to traverse them safely.

### Map Area Geology:

Mapping this area was not possible, there is very little outcrop on either side of Free Gold Creek. The north side of the creek has been thrust up giving a 30-50m cliff. The south side of this east-west creek is low, but gains elevation quickly. Free Gold Creek was traversed from the logging road at 50m elevation to the workings at 350m. And then above the workings to 500m. The creek is very steep and filled with timber and boulders and no outcrop is visible. A small slide above the workings on the south side of the creek was the only outcrop.

This outcrop was iron stained diorite which was not seen anywhere else in the area. If this pyritic diorite could be found on the north side of the creek the distance of fault slip could be measured. Unfortunately this area above the workings is very steep and dangerous and no outcrop could be found.

### Reopen and Sample Workings:

There are three tunnels on this claim, With two being drifted from the creek bed. The other working is on a bluff about 10m above the creek. The upper tunnel (#3) has caved in, but was shovelled clear and was sampled at 2.5m intervals. The two tunnels (#1-#2) drifted from the creek bed were completely plugged with debris. Clearing these tunnels proved to be a back breaking job, but was accomplished. This work will only be temporary, the creek is constantly bringing down material. We cleared the workings in August and sampled them, and by our last trip to the claim in November both drifts were filled with water and debris.

### Tunnel #1:

This tunnel was drifted 30m below the vein from the north side of Free Gold Creek. This working follows a fault ( which assayed up to a gram gold per ton ) as it heads to intersect the vein at depth. Where the tunnel crosses a vein it is heavily mineralised with pyrite and malachite. (the latter not visible in the other workings) In this drift a quartz healed Breccia was noted (and sampled) in a short cross cut to the east. As the tunnel follows the vein north it pinches down and disappears. To the south it seems reasonable strong but was only drifted on for 3.5m. With the assay results, I'm confident this is not the same vein that is followed in tunnels #2 & #3

### Tunnel #2:

This tunnel was drifted just below where the vein outcropped and followed the vein for its entire length. This working was heavily timbered and the lagging has caved, but it is still passable, but dangerous. Assay results gave an average grade of .420 opt for 20 m.

### Tunnel #3:

This working was drifted into the vein where it out-cropped. This tunnel is only in 5m long and the vein remains strong. At 2.5m the vein swells to over a meter. The portal of this tunnel had caved in , but was cleared during this program. Assay results were encouraging.

### South open Cut:

These two small open cuts on the south side of Free Gold Creek explore a narrow (5cm) quartz vein. The highest assay was only 174 ppb Au. Interestingly this vein assayed and struck almost exactly as sample 1-4 taken in tunnel #1 on the north side of the creek.

### North Open Cut:

This working is located above tunnel #3 and follows the surface exposure of the vein for 10m. This vein was sampled every 2.5m giving an average grade of .876 opt Au and up to 20 grams silver per ton.

### Soil Sample:

My proposal was for 100 soil samples to discover how far the Free Gold vein has been shifted by a regional fault. This program was started by laying out a soil grid. The grid was started 50m east of the upper workings and ran for 200m west with stations at 10m intervals. This was repeated for 50m ( 5 lines ) to the south. The first soil line was completed with marginal results. The ground was full of roots and boulders and the sampling was very slow. Also the sample quality was poor due to the steep terrain. This program was stopped and a program of moss mat samples was started.

Moss Mat Samples:

This program started with 3 samples being taken on a creek south of and parallel to Free Gold Creek. These first samples are as follows:

1)	94-M-1	105m	91ppb Au
2)	94-M-2	182m	24ppb Au
3)	94-M-3	350m	32ppb Au

Also 2 samples were taken above and below the Free Gold workings:

1)	94-M-4	350m	11 ppb Au
2)	94-M-5	335m	630ppb Au

With these results a program of sampling was started and it was discovered that samples M-2 & M-3 were taken from a parallel creek. ( there are two creeks south of Free Gold Creek less than 100m apart ) The creek farthest south was named Trail Creek ( as it crosses the trail to the showing ) And the other North Trail Creek, both these creeks were sampled at 50m intervals from an elevation of 100m to about 500m ( Unfortunately a big storm was raging as we completed this program, making my altimeter unreliable ) These two creeks were sampled until they disappeared. A total of 14 samples were taken on Trail Creek and 13 on North Trail Creek. All sample locations were flagged.

Prospecting:

The claim area was thoroughly prospected with nothing of significance being discovered. All the area creeks were also prospected, but due to lack of outcrop only one sample was taken. This sample was a piece of rusty quartz found in North Trail Creek. And assayed as follows:

1) 6-1 182m <5ppb Au

Prospecting the valley another quartz vein was discovered and the first assays are as follows:

1) N-1 N/A 2220ppb Au  
2) N-2 N/A 4120ppb Au  
3) N-3 N/A 1220ppb Au

These samples were taken every 2m along the vein. With these results more work was done on the vein. This included following the vein along strike and more sampling. This vein is located beside a logging road in the Bulson Creek valley. This vein only had a strike of 8m to the north where it pinched down and disappeared. To the south the vein heads under the road and into a slough. This vein was called the "New Vein".

New Vein Samples:

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u>
NV-1	10cm	4.5m	Quartz vein	169 ppb
NV-1	5cm	5m	Quartz vein south offset.	749 ppb
NV-3	8cm	6m	Quartz vein	692 ppb
NV-4	10cm	7m	Quartz vein ( in gouge )	152 ppb

This vein strikes 162° and dips 74° to the east. Although this vein assays significant gold, it is narrow, and with a strike of only 8m it is not recommended for further work.



## Auric Assays

FREE GOLD WORKINGS  
SAMPLES

Tunnel #1:

<u>Sample #</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
1-1	2cm	5m	Quartz vein, strike 190` dip 52`.	22	<0.2	25
1-2	32cm	10m	Quartz in gouge. (stoped)	786	0.6	19
1-3	30cm	15m	Quartz in gouge. (stoped)	984	0.4	82
1-4	4cm	20m	Located in a short crosscut.	7	0.3	120
1-5	30cm	25m	Quartz in gouge. (stoped)	<5	<0.2	48
1-6	30cm	30m	Quartz in gouge. (stoped)	89	<0.2	64
1-7	16cm	40m	Quartz vein, with malachite.	24	0.4	2104
1-8	16cm	40m	Hanging wall of sample 1-7.	<5	<0.2	307
1-9	8cm	40m	Short drift to the south at 2.5m.	15	2.1	13742

FREE GOLD WORKINGS  
SAMPLES

Tunnel #1 Continued:

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
1-10	5cm	40m	Short drift to the south at 3.5m	9	0.4	28
1-11	2m	45m	Quartz healed Breccia.	<5	<0.2	46
1-12	5cm	40m	Pyrite in granite.	24	<0.2	178
1-13	15cm	48m	Quartz vein. (north crosscut)	12	0.3	903
1-14	6cm	50m	Quartz vein. (north crosscut)	13	<0.2	20
1-15	6cm	60m	Quartz vein. (north crosscut)	<5	<0.2	85
1-16	N/A	N/A	Float in creek, (at #1 portal)	3823	0.9	32

FREE GOLD WORKINGS  
SAMPLES

Tunnel #2:

<u>Sample #</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
2-1	6cm	2.5m	Rusty quartz vein.	9335	1.1	32
2-2	8cm	5m	Rusty quartz vein.	7787	1.2	14
2-3	8cm	7.5m	Rusty quartz vein.	.753 (opt)	8.6	25
2-4	8cm	10m	Rusty quartz vein.	6932	2.7	18
2-5	10cm	12.5m	Rusty quartz vein.	.694 (opt)	6.3	46
2-6	8cm	15m	Rusty quartz vein.	8013	1.4	24
2-7	16cm	17.5m	Rusty quartz vein.	9891	0.9	15
2-8	30cm	20m	Rusty quartz vein.	.688 (opt)	3.8	55

\*Note: This vein continues in this working, but was unsafe to sample. This tunnel is in very poor condition and should not be entered until it is rehabilitated!

FREE GOLD WORKINGS  
SAMPLES

Tunnel #3:

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
3-1	11cm	0m	Banded quartz vein. (at portal)	8726	2.7	23
3-2	1m	2.5m	Banded quartz vein.	5757	1.8	19
3-3	13cm	4.5m	Banded quartz vein. (at face)	9214	1.2	14
3-4	N/A	4.5m	Grab. (at face)	4679	1.0	41
3-5	N/A	0m	Grab. (at portal)	.451 (opt)	1.6	43

South Open Cut:

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
5-1	5cm	N/A	Quartz vein. (upper)	19	<0.2	25
5-2	5cm	N/A	Quartz vein. (lower)	174	0.2	152

\*Note: Sample 5-2 was taken 2m lower than 5-1.

FREE GOLD WORKINGS  
SAMPLES

North Open Cut:

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (0pt)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
4-1	25cm	0m	Banded quartz vein. (pyrite)	2.094	20.7	18
4-2	13cm	2.5m	Bull quartz.	0.490	6.5	43
4-3	19cm	7.5m	Banded bull quartz.	0.553	4.3	38
4-4	12cm	10m	Banded quartz vein. (pyrite)	1.014	6.4	32
4-5	N/A	12.5m	Float.(above open cut)	609 (ppb)	0.3	32

\*Note: There was no outcrop at 5m.


\*Note: This open cut is caved at 12.5m.

6-1	N/A	N/A	Float from NTC	<5 (ppb)	<0.2	13
-----	-----	-----	----------------	-------------	------	----

*Workings Maps Auric Claim*


# FREE GOLD TUNNEL #1

Drawn by S.Salmon ( 1994 )  
Area on map 92F5



# FREE GOLD TUNNEL #3

Drawn by S.Salmon ( 1994 )





# FREE GOLD TUNNEL #2

Drawn by S.Salmon ( 1994 )  
Area on map 92F5

3.5m Incline  
+44 degrees

Sample 2-8 at 20m  
Au .688 oz/ton

Sample 2-7 at 17.5m  
Au .288 oz/ton

Sample 2-6 at 15m  
Au .233 oz/ton

Sample 2-5 at 12.5m  
Au .694 oz/ton

Sample 2-4 at 10m  
Au .201 oz/ton

Quartz vein 80'

Sample 2-3 at 7.5m  
Au .753 oz/ton

Lagging caved

Sample 2-2 at 5m  
Au .227 oz/ton

Average grade  
.420 oz/ton


Sample 2-1 at 2.5m  
Au .271 oz/ton

Adit #2

Elevation 370m




Scale 1cm= 1m





# FREE GOLD WORKINGS SOUTH OPEN CUT


Drawn by S.Salmon ( 1994 )







# FREE GOLD WORKINGS NORTH OPENCUT


Drawn by S.Salmon (1994 )





-  GRANITIC ROCK WITH SMALL BODIES AND ANGULAR FRAGMENTS OF ALTERED VOLCANICS
-  QUARTZ AND GOUGE
-  SHEARED ZONE OR FAULT
-  OUTCROP BOUNDARY (APPROX)

FREE GOLD WORKINGS



CONTOUR INTERVAL 50 FEET (APPROX.)

Auric Claim Moss Mats

## Moss Mats


<u>Sample#</u>	<u>AU</u> (ppb)	<u>AS</u> (ppm)	<u>Distance</u>	<u>Sample#</u>	<u>AU</u> (ppb)	<u>AS</u> (ppm)	<u>Distance</u>
TCM-1	6	26	0m	NTCM-1	<5	10	0m
TCM-2	1455	19	50m	NTCM-2	<5	22	50m
TCM-3	<5	17	100m	NTCM-3	6	11	100m
TCM-4	29	10	150m	NTCM-4	12	15	150m
TCM-5	19	19	200m	NTCM-5	<5	13	200m
TCM-6	1039	16	250m	NTCM-6	<5	11	250m
TCM-7	87	<5	300m	NTCM-7	40	6	300m
TCM-8	85	5	350m	NTCM-8	<5	11	350m
TCM-9	144	7	400m	NTCM-9	<5	17	400m
TCM-10	24	7	450m	NTCM-10	6	16	450m
TCM-11	<5	7	500m	NTCM-11	<5	43	500m
TCM-12	<5	7	550m	NTCM-12	<5	48	550m
TCM-13	12	7	600m	NTCM-13	<5	71	600m
TCM-14	9	6	650m				

TCM-Trail Creek Moss  
 NTCM-North Trail Creek Moss


Other Moss Mats

<u>Sample#</u>	<u>AU</u> (ppb)	<u>AS</u> (ppb)	<u>Comments</u>
94-M-1	148	10	Sample from the creek north of Free Gold Creek.
94-M-2	398	22	Free Gold Creek at road.
94-M-3	79	45	New Vein Creek.

# FREE GOLD MOSS MAT SAMPLES:



# FREE GOLD MOSS MAT SAMPLES:






### Conclusions On the Auric Claim

This claim shows promising assays in gold and silver, however due to its location it is not likely to get much attention until land use disputes in the area can be properly settled. The main purpose of this program was to sample the workings and find the continuation of the vein. The workings where sampled with encouraging results and prove the vein carries consistent gold. The moss mat program did indicate an area of anomalous gold in the two creeks south of the workings, and these results will be followed up on in the summer of 1995. The "New vein" discovered during this program does not warrant further work due to its low gold values and short strike length.

Thank you for excepting my application

A handwritten signature in black ink, appearing to read "D. L. ...". The signature is fluid and cursive, with a long horizontal stroke at the end.

Program Completion  
On the Overlord Claim  
Cypress Bay, Catface Range  
Western Vancouver Island, B.C.  
Alberni Mining Division  
NTS 92F/5W  
S.Salmon Prospector 10/12/94

## Overlord Work Program

### Good Hope Adit:

The main adit on the claim is 244m long, This tunnel was filled with water and the portal was blocked by debris. A tree had fallen across the portal and was removed by chainsaw, axe and come along. Then we shovelled the entrance clear allowing most of the water to drain. Then by compass and hip chain the tunnel was mapped. Unfortunately the work done in this working failed to find ore. Although a 30cm vein was stoped out . Sample 94R-13 (vein #6)

### Incline:

This working was reported to be 18m long and on ore. The "Incline" vein is 1m wide and was exposed for 9m. This working was filled with water. When we pumped it out ,we realized that either the incline had caved or this was not the right working. (although the dip and strike are close) The only location given for the incline was in the minister of mines report and are misleading. From the amount of tailings this would seem to be an open-cut, but the vein description seems to fit, and being that they were mining a 1m vein half of the mined material would have been taken as ore. Two days were spent looking for another working but none was found. The search was difficult because of thick brush and the fact that any blazed tree or trail has disappeared over the past hundred. Samples 94R-1 through 4.

### Shaft:

This working is located on a knoll with an open cut blasted in from the north. We spent a day pumping out this shaft. It is 8m deep and was heavily timbered. This shaft was to explore a 1.2m vein exposed just west of the working. Unfortunately this working was to dangerous to enter. Sample 94R-10.

Beach Tunnel:

This working is right on tide water and was to explore a well mineralized vein 25cm wide with a strike length of 5m. Sample 94R-11 & 12.

Shear Zone:

This showing is located on the south- east slope of Cat-face mountain. Where a shear zone outcrops in a steep unnamed creek. Unfortunately this showing was inaccessible due to high water. Although two attempts were made.

OVERLORD SAMPLES

<u>Sample#</u>	<u>Width</u>	<u>Distance</u>	<u>Comments</u>	<u>AU</u> (ppb)	<u>AG</u> (ppm)	<u>CU</u> (ppm)
<u>Incline:</u>						
94R-1	1m	0m	Quartz vein, strike 80 dip 40 SW	15	0.4	154
94R-2	1m	2.5m	Footwall	21	1.9	3092
94R-3	1m	5m	Footwall	95	4.6	9514
94R-4	1m	9m	Face	143	3.9	5404
<u>Vein #1</u>						
94R-5	20cm	N/A	Quartz vein, strike 150` dip 40` SW	22	4.2	5833
<u>Outcrop (above #1 vein)</u>						
94R-6	N/A	N/A	Country rock.	54	0.8	1381
<u>Vein #2</u>						
94R-7	50cm	N/A	Quartz vein, strike N dip 80` E	1010	41.2	4.47%


Sample#	Width	Distance	Comments	AU (ppb)	AG (ppm)	CU (ppm)
<u>Vein #3 (above incline)</u>						
94R-8	25cm	N/A	Quartz vein, with pyrite, calcopyrite.	204	8.4	11021
94R-9	5cm	N/A	Shear zone, strike n dip 85° W	13	3.0	10512
<u>Vein #4 (shaft)</u>						
94R-10	1.2m	N/A	Quartz vein, srike 150° dip 80° S	20	4.2	3263
<u>Vein #5 ( beach tunnel )</u>						
94R-11	25cm	0m	Quartz vein, strike 140° dip 60° W	15	3.3	7792
94R-12	10cm	3m	Sample taken at the face.	473	17.1	3.57%
<u>Vein #6 ( main tunnel )</u>						
94R-13	30cm	N/A	Quartz vein, located in main drift.	31	14.2	2.52%

*Workings Map on The Overlord Claim*

# OVERLORD ("GOOD HOPE") WORKINGS

Drawn by S.Salmon ( 1994 ) Area on map 92F5E

Page 24






### Conclusions On The Overlord Claim

The work on this claim was to accurately sample and map the known veins and workings. This was completed with discouraging results. The grade reported in the old minister of mines reports was 1/3 of an ounce gold 2 ounces silver and 6% copper, these assays could not be duplicated. With my highest assay being 1010 ppb gold 41.2 grams silver and 4.47% copper. The copper grades are high but the gold is too low to be commercial. I think this claim warrants further work, but is in a difficult location and disputed area. The shear zone was not sampled due to high water in the creek where it outcrops. This area will be explored this summer and has some interesting possibilities, being on the contact of the catface intrusion and less than 500m from the 220 million ton Catface deposit.

Thank you for accepting my application

A handwritten signature in black ink, appearing to read "Si Sah". The signature is fluid and cursive, with a long horizontal stroke at the end.

**BRITISH COLUMBIA  
PROSPECTORS ASSISTANCE PROGRAM  
PROSPECTING REPORT FORM (continued)**

**B. TECHNICAL REPORT**

- \* One technical report to be completed for each project area
- \* Refer to Program Requirements/Regulations, section 15, 16 and 17
- \* If work was performed on claims a copy of the applicable assessment report may be submitted in lieu of the supporting data (see section 16) required with this TECHNICAL REPORT

Name Simon Salmon Reference Number 94-95-P60

**LOCATION/COMMODITIES**

Project Area (as listed in Part A.) Tofino Minfile No. if applicable 205-154

Location of Project Area NTS \_\_\_\_\_ Lat \_\_\_\_\_ Long \_\_\_\_\_

Description of Location and Access The Auric claim is located east of Bulson creek in Warn Bay. Access is by boat or barge from Tofino.

The Overlord claim is in Cypress Bay on the east flank of Catface mountain. Access is by boat or plane only.

Main Commodities Searched For Au Ag Cu

Known Mineral Occurrences in Project Area Au Ag Cu

**WORK PERFORMED**

1. Conventional Prospecting (area) \_\_\_\_\_
2. Geological Mapping (hectares/scale) \_\_\_\_\_
3. Geochemical (type and no. of samples) \_\_\_\_\_
4. Geophysical (type and line km) \_\_\_\_\_
5. Physical Work (type and amount) \_\_\_\_\_
6. Drilling (no. holes, size, depth in m, total m) \_\_\_\_\_
7. Other (specify) \_\_\_\_\_

**SIGNIFICANT RESULTS (if any)**

Commodities Au Ag Cu Claim Name Auric/Overlord

Location (show on map) Lat \_\_\_\_\_ Long \_\_\_\_\_ Elevation \_\_\_\_\_

Best assay/sample type Auric 2.091 Oz/Ton Au 20.7 grams/Ton Ag  
Overlord 1 gram/Ton Au 41 grams/Ton Ag 4.47% Cu

Description of mineralization, host rocks, anomalies \_\_\_\_\_



## GEOCHEMICAL ANALYSIS CERTIFICATE



Simon Salmon File # 94-2791

2 - 1157 McClure St., Victoria BC V8V 3G3

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
N-1	2	70	5	64	.1	46	23	390	5.11	9594	<5	<2	<2	55	<.2	8	2	72	1.23	.022	<2	31	1.83	24	.01	7	1.53	<.01	.11	<1	2220
N-2	3	42	7	35	.1	24	11	315	3.66	10396	<5	5	<2	72	<.2	12	<2	31	1.16	.010	<2	16	.59	17	<.01	4	.61	.01	.05	<1	4120
N-3	1	20	5	55	.1	12	8	318	3.09	3207	<5	<2	<2	4	<.2	7	<2	57	.07	.005	<2	10	1.13	10	<.01	6	1.20	<.01	.03	<1	1220
RE N-3	1	18	5	56	.1	13	8	310	3.07	3227	<5	2	<2	4	<.2	7	<2	57	.06	.006	<2	9	1.14	10	<.01	5	1.20	<.01	.03	<1	1180

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.

THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.

ASSAY RECOMMENDED FOR ROCK AND CORE SAMPLES IF CU PB ZN AS &gt; 1%, AG &gt; 30 PPM &amp; AU &gt; 1000 PPB

- SAMPLE TYPE: ROCK AU\* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE. Samples beginning 'RE' are duplicate samples.

DATE RECEIVED: AUG 23 1994

DATE REPORT MAILED: Aug 31/94.

SIGNED BY.....D.TOYE, C.LEONG, J.WANG; CERTIFIED B.C. ASSAYERS



## GEOCHEMICAL ANALYSIS CERTIFICATE



Simon Salmon File # 94-3468

2 - 1157 McClure St., Victoria BC V8V 3G3

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au* ppb
94-M-1	1	38	9	52	.1	16	16	1149	1.83	25	8	<2	<2	50	.2	<2	<2	48	1.80	.068	6	33	.31	39	.05	10	2.66	.01	.04	<1	91
94-M-2	1	25	8	60	<.1	15	15	904	3.06	10	<5	<2	<2	29	<.2	<2	<2	109	.81	.037	5	43	.25	24	.08	5	2.32	.01	.04	<1	24
94-M-3	3	27	13	58	<.1	12	12	914	3.69	<2	<5	<2	<2	23	<.2	<2	8	118	.64	.041	5	49	.29	32	.10	<2	3.02	<.01	.04	<1	32
94-M-4	<1	72	<2	71	.1	20	17	1096	3.20	8	<5	<2	<2	35	<.2	<2	<2	71	1.19	.069	7	33	.86	37	.08	7	2.63	.02	.08	<1	11
94-M-5	<1	97	11	75	.2	29	20	1119	4.05	17	5	<2	<2	37	1.1	<2	3	99	1.05	.054	6	42	.95	34	.12	3	2.59	.01	.04	<1	630
RE 94-M-5	<1	93	15	71	.3	26	18	1073	3.84	15	5	<2	<2	35	1.2	<2	<2	94	1.01	.052	5	40	.89	31	.11	5	2.46	.01	.04	<1	1090
STANDARD C/AU-S	18	56	39	128	6.6	71	32	1054	3.96	43	22	6	35	50	17.6	14	18	60	.49	.090	39	58	.93	182	.08	35	1.88	.06	.15	11	47

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.  
THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL.

- SAMPLE TYPE: MOSS MAT AU\* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE. Samples beginning 'RE' are duplicate samples.

DATE RECEIVED: OCT 3 1994

DATE REPORT MAILED: Oct 12/94

SIGNED BY: *C. King* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

CLIENT: BEAU PRE EXPLORATIONS LTD.  
REPORT: V94-01366.6 ( COMPLETE )

PROJECT: NONE GIVEN  
DATE PRINTED: 30-DEC-94 PAGE 1

SAMPLE NUMBER	ELEMENT UNITS	Au OPT	Cu PCT
R2 2-3		0.753	
R2 2-5		0.694	
R2 2-8		0.688	
R2 3-5		0.451	
R2 4-1		2.094	
R2 4-2		0.490	
R2 4-3		0.553	
R2 4-4		1.014	
R2 94-R 7			4.47
R2 94-R 12			3.57
R2 94-R 13			2.52

CLIENT: BEAU PRE EXPLORATIONS LTD.

PROJECT: NONE GIVEN

REPORT: V94-01366.0 ( COMPLETE )

DATE PRINTED: 15-DEC-94

PAGE 1A

SAMPLE NUMBER	ELEMENT UNITS	Au10 PPB	AuRes1 PPB	Ag PPM	Cu PPM	Pb PPM	Zn PPM	Mb PPM	Ni PPM	Co PPM	Cd PPM	Bi PPM	As PPM
R2 NV-1		169		0.2	115	<	88	5	38	24	<1.0	<	110
R2 NV-2		749		<0.2	51	<	49	9	14	8	<1.0	<	418
R2 NV-3		692		0.2	152	<	118	6	39	26	<1.0	<	199
R2 NV-4		152		0.3	94	4	96	4	42	23	<1.0	<	176
R2 1-1		22		<0.2	25	2	31	7	5	6	<1.0	<	15
R2 1-2		786		0.6	19	6	59	6	35	24	<1.0	<	159
R2 1-3		984	989	0.4	82	8	80	2	45	23	<1.0	<	163
R2 1-4		7		0.3	120	7	125	4	6	22	<1.0	<	25
R2 1-5		<		<0.2	48	4	88	3	17	23	<1.0	<	12
R2 1-6		89		<0.2	64	10	118	2	22	22	<1.0	<	53
R2 1-7		24		0.4	2104	<	75	5	34	25	<1.0	<	24
R2 1-8		<		<0.2	307	2	57	3	4	17	<1.0	<	13
R2 1-9		15		2.1	13742	8	29	4	12	11	<1.0	<	10
R2 1-10		9		0.4	28	6	20	<	<	1	<1.0	<	<
R2 1-11		<		<0.2	46	3	79	4	75	24	<1.0	<	13
R2 1-12		24		<0.2	178	4	45	3	9	9	<1.0	<	23
R2 1-13		12		0.3	903	3	38	5	5	19	<1.0	<	9
R2 1-14		13		<0.2	20	<	14	7	3	3	<1.0	<	<
R2 1-15		<		<0.2	85	20	105	3	3	20	<1.0	<	17
R2 1-16		3823		0.9	32	7	24	8	4	3	1.3	<	47
R2 2-1		9335		1.1	32	12	36	11	4	4	1.0	<	67
R2 2-2		7787		1.2	14	5	20	4	5	3	5.7	<	40
R2 2-3		>10000		8.6	25	561	332	7	4	3	37.3	<	94
R2 2-4		6932		2.7	18	30	19	9	2	3	3.0	<	65
R2 2-5		>10000		6.3	46	240	227	5	7	3	49.7	<	96
R2 2-6		8013		1.4	24	98	74	8	3	3	19.0	<	31
R2 2-7		9891		0.9	15	22	22	8	4	4	2.3	<	60
R2 2-8		>10000		3.8	55	41	55	3	9	9	5.8	<	87
R2 3-1		8726		2.7	23	121	20	8	3	2	3.8	<	44
R2 3-2		5757	5474	1.8	19	25	35	4	10	7	2.2	<	77
R2 3-3		9214		1.2	14	40	24	7	12	7	3.2	<	80
R2 3-4		4679		1.0	41	5	33	7	8	6	3.9	<	71
R2 3-5		>10000		1.6	43	28	39	6	14	12	1.3	<	94
R2 4-1		>10000		20.7	18	50	28	8	8	8	4.8	<	101
R2 4-2		>10000		6.5	43	103	36	10	8	7	4.9	<	74
R2 4-3		>10000		4.3	38	88	49	4	18	17	11.5	<	148
R2 4-4		>10000		6.4	32	119	25	8	10	10	2.1	<	98
R2 4-5		609		0.3	32	17	17	12	5	3	<1.0	<	11
R2 5-1		19		<0.2	25	3	21	6	10	4	<1.0	<	<
R2 5-2		174		0.2	152	5	113	6	7	24	<1.0	<	32

CLIENT: BEAU PPE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN

DATE PRINTED: 15-DEC-94

PAGE 1B

SAMPLE NUMBER	ELEMENT UNITS	Sb PPM	Hg PPM	Fe PCT	Mn PPM	Te PPM	Ba PPM	Cr PPM	V PPM	Sn PPM	W PPM	La PPM	Al PCT
R2 NV-1		♾	<0.010	5.38	369	<10	17	118	105	<20	<20	19	2.80
R2 NV-2		♾	0.019	1.59	148	<10	16	155	35	<20	<20	5	0.81
R2 NV-3		♾	0.028	5.65	552	<10	16	90	132	<20	<20	21	3.32
R2 NV-4		♾	0.025	6.39	576	<10	34	64	146	<20	<20	26	4.34
R2 1-1		♾	0.124	1.68	652	<10	37	103	12	<20	<20	17	0.92
R2 1-2		♾	0.176	3.59	1264	<10	33	60	38	<20	<20	16	1.83
R2 1-3		♾	0.047	4.13	1136	<10	20	49	44	<20	<20	21	2.46
R2 1-4		♾	0.449	4.58	1667	<10	35	33	98	<20	<20	25	2.89
R2 1-5		♾	0.086	4.33	1271	<10	20	66	95	<20	<20	25	3.10
R2 1-6		♾	0.122	4.13	2200	<10	19	25	67	<20	<20	25	2.51
R2 1-7		♾	0.042	3.08	624	<10	4	102	49	<20	<20	10	2.11
R2 1-8		♾	0.036	2.74	514	<10	13	43	30	<20	<20	13	1.92
R2 1-9		♾	0.218	2.39	285	<10	7	110	14	<20	<20	8	0.81
R2 1-10		♾	0.061	0.57	2103	<10	4	30	6	<20	<20	8	0.26
R2 1-11		♾	0.209	3.33	607	<10	21	105	52	<20	<20	14	2.47
R2 1-12		♾	0.113	1.31	302	<10	16	86	24	<20	<20	7	1.76
R2 1-13		♾	<0.010	2.67	359	<10	4	93	35	<20	<20	9	1.15
R2 1-14		♾	0.026	0.80	311	<10	8	128	11	<20	<20	4	0.39
R2 1-15		♾	0.028	4.52	1385	<10	8	34	73	<20	<20	22	2.50
R2 1-16		♾	0.021	0.47	118	<10	2	188	2	<20	<20	2	0.08
R2 2-1		♾	0.016	0.70	336	<10	10	196	4	<20	<20	3	0.22
R2 2-2		♾	<0.010	0.82	308	<10	8	136	4	<20	<20	4	0.23
R2 2-3		♾	0.621	1.16	428	<10	6	153	8	<20	<20	4	0.28
R2 2-4		♾	0.030	1.10	719	<10	13	161	4	<20	<20	7	0.27
R2 2-5		♾	2.823	1.26	598	<10	10	175	10	<20	<20	7	0.18
R2 2-6		♾	0.081	0.99	391	<10	9	180	7	<20	<20	4	0.26
R2 2-7		♾	<0.010	1.21	395	<10	9	140	7	<20	<20	5	0.41
R2 2-8		♾	0.076	2.58	1096	<10	19	89	21	<20	<20	12	1.09
R2 3-1		♾	0.126	0.64	142	<10	3	176	7	<20	<20	2	0.07
R2 3-2		♾	0.047	1.74	649	<10	13	120	16	<20	<20	7	1.09
R2 3-3		♾	0.023	1.50	513	<10	9	165	14	<20	<20	5	0.52
R2 3-4		♾	0.020	1.41	763	<10	8	132	12	<20	<20	6	0.52
R2 3-5		♾	0.042	2.40	440	<10	8	173	26	<20	<20	8	0.89
R2 4-1		♾	0.246	1.75	401	<10	5	164	22	<20	<20	5	0.68
R2 4-2		♾	0.119	1.50	295	<10	4	186	18	<20	<20	4	0.57
R2 4-3		♾	0.211	2.50	1116	<10	22	120	30	<20	<20	9	1.10
R2 4-4		♾	0.096	1.79	417	<10	8	167	20	<20	<20	6	0.60
R2 4-5		♾	0.022	0.66	311	<10	4	218	8	<20	<20	2	0.21
R2 5-1		♾	0.037	1.29	654	<10	25	225	9	<20	<20	4	0.51
R2 5-2		♾	0.076	6.13	1755	<10	39	65	67	<20	<20	31	2.97

CLIENT: BEAU PRE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN  
 DATE PRINTED: 15-DEC-94 PAGE 1C

SAMPLE NUMBER	ELEMENT UNITS	Mg PCT	Ca PCT	Na PCT	K PCT	Sr PPM	Y PPM
R2 NV-1		2.51	0.10	<0.01	0.09	3	3
R2 NV-2		0.78	0.10	<0.01	0.04	6	1
R2 NV-3		2.84	0.17	0.01	0.07	5	3
R2 NV-4		3.02	0.16	0.01	0.18	5	3
R2 1-1		0.59	0.15	0.01	0.12	5	7
R2 1-2		1.33	3.12	<0.01	0.14	34	6
R2 1-3		1.61	5.12	<0.01	0.15	50	8
R2 1-4		1.91	8.27	<0.01	0.07	83	12
R2 1-5		2.37	4.76	0.02	0.06	49	9
R2 1-6		1.57	>10.00	<0.01	0.10	120	9
R2 1-7		2.37	0.67	<0.01	<0.01	46	2
R2 1-8		1.80	1.23	<0.01	0.07	59	8
R2 1-9		0.90	0.83	<0.01	0.02	44	2
R2 1-10		0.16	>10.00	<0.01	0.01	745	10
R2 1-11		2.26	1.13	0.13	0.06	40	6
R2 1-12		0.61	1.93	0.05	0.03	20	6
R2 1-13		1.14	0.80	<0.01	0.01	67	3
R2 1-14		0.22	2.82	<0.01	0.04	40	2
R2 1-15		1.58	4.20	0.01	0.03	134	7
R2 1-16		0.03	0.05	<0.01	<0.01	2	<1
R2 2-1		0.07	0.07	<0.01	0.04	2	2
R2 2-2		0.06	0.14	<0.01	0.03	5	2
R2 2-3		0.09	0.05	<0.01	0.03	2	2
R2 2-4		0.07	0.75	<0.01	0.05	8	4
R2 2-5		0.03	0.05	<0.01	0.04	2	3
R2 2-6		0.10	0.05	<0.01	0.04	2	2
R2 2-7		0.39	0.30	<0.01	0.03	4	2
R2 2-8		1.14	2.28	<0.01	0.05	16	7
R2 3-1		0.02	0.02	<0.01	0.02	<1	<1
R2 3-2		0.96	0.48	<0.01	0.05	6	5
R2 3-3		0.50	0.41	<0.01	0.03	4	3
R2 3-4		0.46	1.53	<0.01	0.02	14	4
R2 3-5		1.06	0.03	<0.01	0.02	1	2
R2 4-1		0.80	0.03	<0.01	0.02	1	<1
R2 4-2		0.60	0.03	<0.01	<0.01	1	1
R2 4-3		1.05	0.04	<0.01	0.07	2	4
R2 4-4		0.62	0.03	<0.01	0.02	2	2
R2 4-5		0.14	<0.01	<0.01	<0.01	<1	1
R2 5-1		0.22	0.06	<0.01	0.03	2	2
R2 5-2		1.74	0.61	<0.01	0.02	18	15



CLIENT: BEAU FRE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN

DATE PRINTED: 15-DEC-94

PAGE 2A

SAMPLE NUMBER	ELEMENT UNITS	Au10 PPB	AuRwl PPB	Ag PPM	Cu PPM	Pb PPM	Zn PPM	Mo PPM	Ni PPM	Co PPM	Cd PPM	Bi PPM	As PPM
R2 5-3		59		0.3	691	2	81	8	3	25	<1.0	6	22
R2 6-1		<5		<0.2	13	<2	14	6	9	4	<1.0	6	8
R2 94-R 1		15		0.4	154	<2	7	10	4	2	<1.0	6	6
R2 94-R 2		21		1.9	3092	2	41	12	4	7	<1.0	6	6
R2 94-R 3		95		4.6	9514	5	190	6	18	37	4.5	6	6
R2 94-R 4		143		3.9	5404	3	601	13	51	139	18.0	6	6
R2 94-R 5		22		4.2	5833	3	242	15	59	119	5.5	6	6
R2 94-R 6		54		0.8	1381	4	82	2	9	18	<1.0	6	8
R2 94-R 7		1010		41.2	>20000	12	519	6	11	28	18.1	17	6
R2 94-R 8		204		8.4	11021	7	239	3	14	16	7.5	6	6
R2 94-R 9		13		3.0	10512	10	172	3	19	36	4.9	6	6
R2 94-R 10		20		4.2	3263	2	121	12	9	15	1.2	6	6
R2 94-R 11		15		3.3	7792	5	287	7	32	52	2.7	6	10
R2 94-R 12		473		17.1	>20000	13	955	9	81	207	22.1	6	6
R2 94-R 13		31		14.2	>20000	12	317	12	47	189	8.0	6	6
V1 NIOM 1		<5		<0.2	43	6	51	4	12	13	<1.0	6	10
V1 NIOM 2		<5		<0.2	34	11	62	3	11	14	<1.0	6	22
V1 NIOM 3		6		<0.2	30	8	47	2	14	19	<1.0	6	11
V1 NIOM 4		12		<0.2	27	8	59	2	12	14	<1.0	6	15
V1 NIOM 5		<5		<0.2	22	12	45	2	10	13	<1.0	6	13
V1 NIOM 6		<5		<0.2	27	12	55	2	12	19	<1.0	6	11
V1 NIOM 7		40		<0.2	18	16	39	1	6	10	<1.0	6	6
V1 NIOM 8		<5		<0.2	28	13	63	3	12	15	<1.0	6	11
V1 NIOM 9		<5		<0.2	31	14	79	2	11	14	<1.0	6	17
V1 NIOM 10		6		<0.2	31	22	66	2	11	15	<1.0	6	16
V1 NIOM 11		<5		<0.2	41	22	97	3	15	24	<1.0	6	43
V1 NIOM 12		<5		<0.2	49	19	111	2	18	28	<1.0	6	48
V1 NIOM 13		<5		0.2	57	13	80	3	12	37	<1.0	6	71
V1 TOM-1		6		<0.2	34	8	49	2	10	14	<1.0	6	26
V1 TOM-2		1455		<0.2	39	8	53	2	13	19	<1.0	6	19
V1 TOM-3		<5		<0.2	26	8	55	2	12	21	<1.0	6	17
V1 TOM-4		29		<0.2	28	6	46	1	8	13	<1.0	6	10
V1 TOM-5		19		<0.2	35	9	56	2	12	19	<1.0	6	19
V1 TOM-6		1039		<0.2	35	12	61	2	12	25	<1.0	6	16
V1 TOM-7		87		<0.2	33	10	52	2	10	40	<1.0	6	6
V1 TOM-8		85		<0.2	33	11	50	1	9	22	<1.0	6	5
V1 TOM-9		144		<0.2	33	9	52	5	10	32	<1.0	6	7
V1 TOM-10		24		<0.2	33	13	58	2	10	29	<1.0	6	7
V1 TOM-11		<5		<0.2	37	14	55	2	12	26	<1.0	6	7
V1 TOM-12		<5		<0.2	29	7	53	2	12	18	<1.0	6	7

CLIENT: BEAU FRE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN

DATE PRINTED: 15-DEC-94

PAGE 2B

SAMPLE NUMBER	ELEMENT UNITS	Sb PPM	Hg PPM	Fe PCT	Mn PPM	Te PPM	Ba PPM	Cr PPM	V PPM	Sn PPM	W PPM	La PPM	Al PCT
R2 5-3	♣	0.014	5.78	994	<10	9	51	40	<20	<20	31	2.54	
R2 6-1	♣	<0.010	0.83	177	<10	7	190	12	<20	<20	2	0.44	
R2 94-R 1	♣	0.068	0.56	59	<10	<20	213	4	<20	<20	2	0.07	
R2 94-R 2	♣	0.258	1.26	38	<10	<20	193	8	<20	<20	3	0.09	
R2 94-R 3	♣	0.788	5.42	319	<10	5	86	161	<20	<20	21	1.83	
R2 94-R 4	♣	1.615	5.81	185	<10	<20	116	79	<20	<20	19	1.04	
R2 94-R 5	♣	0.450	3.90	79	<10	<20	239	18	<20	<20	11	0.30	
R2 94-R 6	♣	0.075	2.48	278	<10	20	40	81	<20	<20	9	1.08	
R2 94-R 7	♣	2.813	7.41	161	18	7	55	53	<20	<20	25	0.68	
R2 94-R 8	♣	0.783	3.11	123	<10	18	127	57	<20	<20	8	0.60	
R2 94-R 9	♣	0.978	1.92	198	<10	4	43	92	<20	<20	7	2.27	
R2 94-R 10	♣	0.277	1.98	72	<10	<20	216	19	<20	<20	5	0.33	
R2 94-R 11	♣	0.454	5.48	455	<10	<20	69	147	<20	<20	21	2.19	
R2 94-R 12	♣	3.420	7.30	101	17	<20	92	37	<20	<20	27	0.62	
R2 94-R 13	♣	1.033	5.88	135	<10	<20	98	34	<20	<20	20	0.57	
V1 NIEM 1	♣	0.123	2.94	604	<10	22	42	104	<20	<20	11	1.47	
V1 NIEM 2	♣	0.175	1.63	831	<10	33	26	53	<20	<20	10	2.20	
V1 NIEM 3	♣	0.125	3.06	1028	<10	16	36	83	<20	<20	11	1.53	
V1 NIEM 4	♣	0.138	2.39	730	<10	25	33	81	<20	<20	11	2.10	
V1 NIEM 5	♣	0.193	2.17	846	<10	24	28	74	<20	<20	9	1.66	
V1 NIEM 6	♣	0.205	2.86	1237	<10	26	37	98	<20	<20	12	2.07	
V1 NIEM 7	♣	0.496	1.14	1064	<10	25	15	35	<20	<20	5	0.94	
V1 NIEM 8	♣	0.133	2.68	835	<10	29	35	89	<20	<20	13	2.30	
V1 NIEM 9	♣	0.258	1.91	1348	<10	34	26	61	<20	<20	11	2.35	
V1 NIEM 10	♣	0.342	1.63	1591	<10	34	24	52	<20	<20	12	2.52	
V1 NIEM 11	♣	0.278	1.22	2131	<10	36	25	34	<20	<20	13	4.26	
V1 NIEM 12	♣	0.282	0.96	1873	<10	40	28	27	<20	<20	15	4.66	
V1 NIEM 13	♣	0.261	0.88	1436	<10	32	22	26	<20	<20	17	6.86	
V1 TCM-1	♣	0.222	1.42	1169	<10	31	21	39	<20	<20	8	1.85	
V1 TCM-2	♣	0.131	2.35	2811	<10	29	31	70	<20	<20	11	1.62	
V1 TCM-3	♣	0.158	2.34	1046	<10	27	32	84	<20	<20	12	2.11	
V1 TCM-4	♣	0.183	1.23	932	<10	21	17	34	<20	<20	7	1.23	
V1 TCM-5	♣	0.206	2.00	1305	<10	26	29	62	<20	<20	10	1.63	
V1 TCM-6	♣	0.175	1.91	1623	<10	28	27	56	<20	<20	10	1.86	
V1 TCM-7	♣	0.238	1.79	2188	<10	31	17	56	<20	<20	9	1.50	
V1 TCM-8	♣	0.242	1.05	1905	<10	37	10	27	<20	<20	7	1.21	
V1 TCM-9	♣	0.250	1.46	2048	<10	35	15	39	<20	<20	8	1.58	
V1 TCM-10	♣	0.270	1.64	2886	<10	27	17	42	<20	<20	9	1.52	
V1 TCM-11	♣	0.378	2.42	1710	<10	22	28	76	<20	<20	11	1.62	
V1 TCM-12	♣	0.142	2.14	1052	<10	24	26	66	<20	<20	10	1.60	

CLIENT: BEAU PRE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN

DATE PRINTED: 15-DEC-94

PAGE 2C

SAMPLE NUMBER	ELEMENT UNITS	Mg PCT	Ca PCT	Na PCT	K PCT	Sr PPM	Y PPM
R2 5-3		1.98	1.28	<0.01	<0.01	70	20
R2 6-1		0.25	0.01	<0.01	0.04	<1	<1
R2 94-R 1		0.02	0.02	<0.01	<0.01	<1	<1
R2 94-R 2		0.02	0.03	<0.01	<0.01	2	<1
R2 94-R 3		1.42	0.33	<0.01	0.02	3	3
R2 94-R 4		0.94	0.46	0.01	0.03	4	3
R2 94-R 5		0.16	0.20	<0.01	<0.01	1	<1
R2 94-R 6		0.86	1.49	0.06	0.04	17	9
R2 94-R 7		0.25	0.56	0.02	0.01	13	<1
R2 94-R 8		0.49	0.27	0.03	0.02	7	2
R2 94-R 9		0.16	3.67	0.01	0.01	6	3
R2 94-R 10		0.12	0.18	<0.01	<0.01	3	1
R2 94-R 11		2.05	0.89	0.01	0.05	11	5
R2 94-R 12		0.59	0.40	0.02	0.07	9	3
R2 94-R 13		0.42	0.60	0.01	0.03	3	1
V1 NTCM 1		0.35	0.57	0.01	0.03	24	3
V1 NTCM 2		0.21	1.19	0.01	0.04	43	6
V1 NTCM 3		0.64	0.45	0.02	0.07	20	3
V1 NTCM 4		0.28	0.71	0.01	0.05	28	5
V1 NTCM 5		0.25	0.55	0.01	0.08	23	4
V1 NTCM 6		0.21	0.53	0.01	0.06	23	6
V1 NTCM 7		0.13	0.88	0.01	0.12	31	3
V1 NTCM 8		0.26	0.70	0.01	0.04	27	6
V1 NTCM 9		0.20	0.97	0.02	0.08	34	7
V1 NTCM 10		0.15	0.91	0.02	0.13	33	8
V1 NTCM 11		0.13	0.85	0.01	0.07	35	11
V1 NTCM 12		0.11	1.14	0.01	0.11	42	13
V1 NTCM 13		0.05	0.66	0.01	0.12	29	15
V1 TCM-1		0.33	1.43	0.02	0.09	48	4
V1 TCM-2		0.69	0.87	0.02	0.10	32	3
V1 TCM-3		0.24	0.62	0.02	0.07	31	5
V1 TCM-4		0.29	0.80	0.02	0.18	31	3
V1 TCM-5		0.50	0.78	0.02	0.13	35	3
V1 TCM-6		0.43	0.72	0.02	0.10	32	4
V1 TCM-7		0.33	0.67	0.02	0.16	33	3
V1 TCM-8		0.26	0.80	0.02	0.12	37	4
V1 TCM-9		0.33	0.73	0.03	0.16	34	4
V1 TCM-10		0.43	0.69	0.04	0.32	29	3
V1 TCM-11		0.59	0.55	0.02	0.13	25	3
V1 TCM-12		0.62	0.62	0.02	0.08	26	3

CLIENT: BEAU PRE EXPLORATIONS LTD.  
 REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN  
 DATE PRINTED: 15-DEC-94 PAGE 3A

SAMPLE NUMBER	ELEMENT UNITS	Au10 PPB	AuRe-1 PPB	Ag PPM	Cu PPM	Pb PPM	Zn PPM	Mo PPM	Ni PPM	Co PPM	Cd PPM	Bi PPM	As PPM
V1 TCM-13		12		<0.2	32	10	53	1	10	23	<1.0	6	7
V1 TCM-14		9		<0.2	35	13	46	2	8	23	<1.0	6	6
V1 94-1		148		<0.2	38	7	52	1	6	12	<1.0	6	10
V1 94-2		398		0.2	66	6	66	1	15	19	<1.0	6	22
V1 94-3		79		<0.2	55	6	96	<1	15	16	<1.0	6	45

CLIENT: BEAU PPE EXPLORATIONS LTD.  
REPORT: V94-01366.0 { COMPLETE }

PROJECT: NONE GIVEN  
DATE PRINTED: 15-DEC-94 PAGE 3B

SAMPLE NUMBER	ELEMENT UNITS	Sb PPM	Hg PPM	Fe PCT	Mn PPM	Te PPM	Ba PPM	Cr PPM	V PPM	Sn PPM	W PPM	La PPM	Al PCT
V1 TCM-13		<S	0.264	1.93	1713	<10	29	21	56	<20	<20	10	1.69
V1 TCM-14		<S	0.453	1.83	1728	<10	28	16	45	<20	<20	10	1.67
V1 94-1		<S	0.151	2.23	1311	<10	46	7	49	<20	<20	12	1.52
V1 94-2		<S	0.187	3.21	887	<10	26	35	84	<20	<20	15	2.21
V1 94-3		<S	0.147	2.43	1377	<10	37	28	65	<20	<20	12	2.08

CLIENT: BEAU PRE EXPLORATIONS LTD.  
REPORT: V94-01366.0 ( COMPLETE )

PROJECT: NONE GIVEN  
DATE PRINTED: 15-DEC-94 PAGE 3C

SAMPLE NUMBER	ELEMENT UNITS	Mg PCT	Ca PCT	Na PCT	K PCT	Sr PPM	Y PPM
V1 TCM-13		0.39	0.72	0.02	0.15	30	4
V1 TCM-14		0.27	0.66	0.02	0.13	25	4
V1 94-1		0.67	0.43	0.02	0.15	27	5
V1 94-2		0.88	0.96	0.02	0.08	35	5
V1 94-3		0.87	1.39	0.02	0.20	42	4