

BRITISH COLUMBIA
PROSPECTORS ASSISTANCE PROGRAM
MINISTRY OF ENERGY AND MINES
GEOLOGICAL SURVEY BRANCH

PROGRAM YEAR: 1997/1998

REPORT #: PAP 97-30

NAME: ARNOLD SAVJORD

BRITISH COLUMBIA
PROSPECTORS ASSISTANCE PROGRAM
PROSPECTING REPORT FORM (continued)

B. TECHNICAL REPORT

- One technical report to be completed for each project area.
- Refer to Program Requirements/Regulations, section 15, 16 and 17.
- If work was performed on claims a copy of the applicable assessment report may be submitted in lieu of the supporting data (see section 16) required with this TECHNICAL REPORT.

Name A. SAVJORD Reference Number 97/98 - P75

LOCATION/COMMODITIES

Project Area (as listed in Part A) SLOCAN-KAMI 5 MINFILE No. if applicable _____

Location of Project Area NTS 82 E 16 W Lat _____ Long _____

Description of Location and Access By Highway 6 from Numbly to summit of Monarch - south on Red THE VALLEY Road - 4 miles to Rio Logging road - then 2.5 km on Rio to end of Road

Main Commodities Searched For GOLD - SILVER

Known Mineral Occurrences in Project Area _____

WORK PERFORMED

1. Conventional Prospecting (area) General area
2. Geological Mapping (hectares/scale) _____
3. Geochemical (type and no. of samples) _____
4. Geophysical (type and line km) Soil sampling - 100m along fault zone
5. Physical Work (type and amount) Stream sampling 200' above on zone
6. Drilling (no., holes, size, depth in m, total m) _____
7. Other (specify) Spill, Blast residue waste - 300 Ton

SIGNIFICANT RESULTS

Commodities GOLD SILVER Claim Name KAMI 5

Location (show on map) Lat _____ Long _____ Elevation 5500

Best assay/sample type 4 03 GOLD - 46 03 SILVER

Description of mineralization, host rocks, anomalies see report - MIKE CATHERO

Supporting data must be submitted with this TECHNICAL REPORT
Information on this form is confidential for one year from the date of receipt subject to the provisions of the Freedom of Information Act.

4-Nov-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 97-1223

TOTAL DIGESTION

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

ATTENTION: ARNOLD SAVJORD

Phone: 604-573-5700
Fax : 604-573-4557


Rodes - main trench

No. of samples received: 3
Sample type: ROCK
PROJECT #: KAMI 5 PROPERTY
SHIPMENT #: NONE GIVEN
Samples submitted by: MIKE CATHRO

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sr	Ti %	V	W	Y	Zn
1	K1	>30	0.73	200	15	1.35	>1000	31	167	650	>10	0.27	0.03	1399	<1	0.02	10	<10	>10000	117	0.02	6	<10	<1	>10000
2	K2	14.4	9.34	800	20	3.24	7	7	134	<1	2.44	3.23	0.68	990	3	0.09	3	810	328	202	0.15	10	<10	13	343
3	K3	>30	0.84	150	10	0.09	<1	9	259	<1	4.48	0.29	0.05	84	7	0.02	7	20	382	57	0.02	6	20	4	106
QC DATA:																									
Resplit:																									
1	K1	>30	0.63	185	<5	1.16	>1000	28	150	619	>10	0.25	0.03	1198	<1	0.02	10	<10	>10000	111	0.02	5	<10	<1	>10000
Repeat:																									
1	K1	>30	0.70	190	5	1.24	>1000	29	161	608	>10	0.27	0.03	1295	<1	0.02	6	<10	>10000	109	0.02	5	<10	<1	>10000
Standard:																									
STSD-2		0.5	4.40	425	35	2.50	8	18	105	35	5.00	1.2	1.80	890	10	0.09	49	1140	68	370	0.49	101	<10	40	240
STSD-3		0.4	3.76	1335	20	2.28	1	15	72	32	4.80	1.4	1.40	2845	6	0.82	26	1350	46	230	0.39	140	<10	38	209
STSD-4		0.3	3.40	1815	10	2.60	7	12	90	50	4.34	1.2	1.20	1557	<1	1.40	24	800	20	320	0.42	111	<10	28	100

df/1223
XLS/97
fax: 573-1724

per

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

4-Nov-97

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

CERTIFICATE OF ANALYSIS AK97-1223

ATTENTION: ARNOLD SAVJORD

No. of samples received: 3
Sample type: Rock
PROJECT #: Kami 5 Property
SHIPMENT #: Not Given
Samples submitted by: M. Cathro

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	As	Hg(ppb)	Sb	Te	Se
1	K1	>30	504	435	33	6.2	2.2
2	K2	-	74	25	0.3	-	-
3	K3	-	350	20	0.8	-	-

QC DATA:

Resplit:


R/S 1	K1	>30	529	460	38	-	-
-------	----	-----	-----	-----	----	---	---

Repeat:

1	K1	>30	571	435	32	6.4	2.3
---	----	-----	-----	-----	----	-----	-----


Standard:

GEO'97	1.4	59	-	3	0.5	0.2
SO2	-	-	82	-	-	-
SO3	-	-	17	-	-	-



ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97- 1223

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

29-Oct-97

ATTENTION: ARNOLD SAVJORD


No. of samples received: 3
Sample type: Rock
PROJECT #: Kami 5 Property
SHIPMENT #: Not Given
Samples submitted by: M. Cathro

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cd (%)	Pb (%)	Zn (%)
1	K1	39.59	1.155	1000.0	29.16	0.164	5.08	7.60
2	K2	1.01	0.029	-	-	-	-	-
3	K3	0.83	0.024	52.4	1.53	-	-	-

QC/DATA:

Repeat:								
2	K2	0.94	0.027	-	-	-	-	-
Resplit:								
R/S 1	K1	-	-	-	-	-	5.08	7.60
Standard:								
STD-M		1.60	0.047	-	-	-	-	-
CPb-1		-	-	-	-	-	-	4.42
MP-1a		-	-	69.7	2.03	-	4.33	19.02
CZN-1		-	-	-	-	0.134	-	-

NOTE: * = Metallic Screen Assay -Au

per 
EGO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97-1158

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

8-Oct-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 1
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: ARNOLD

rock (main trench)

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	NEW VEIN	6.62	0.193	324.0	9.36

QC/DATA:

Repeat:

1	NEW VEIN	6.78	0.198	319.0	9.30
---	----------	------	-------	-------	------


Resplit:


1	NEW VEIN	7.22	0.211	324.0	9.45
---	----------	------	-------	-------	------

Standard:

STD-M		1.38	0.040	-	-
Mp-la		-	-	70.0	2.04

XLS/97
fax: 573-1724

per 
ECO-TECH LABORATORIES LTD
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

13041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97-1057

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

29-Sep-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 4
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: Arnold Savjord
rocks-main trench

Post-It Fax Note	7671E	Date	Sep 30	# of pages	3
To	Arnold	From			
Co./Dept.		Co.			
Phone #		Phone #			
Fax #		Fax #			


ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	BAN COMP	54.60	1.592	1380	40.25
2	BAN NEW	19.10	0.557	1020	29.75
3	BAN FOOT	0.18	0.005	22.6	0.66
4	BAN TOP	0.26	0.008	15.4	0.45

QC/DATA:

Resplit:
1 BAN COMP 55.10 1.607 1390 40.54

Repeat:
1 BAN COMP 55.80 1.627 1390 40.54

Standard:
STD-M 1.49 0.043


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97- 1166

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

9-Oct-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 1
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: ARNOLD

*rock - same loc. as K-1 (grab).
GRAB SAMPLE sulphide rich*


ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	BLUE VEIN 2	138.4	4.036	1630	47.54

QC/DATA:

Repeat:					
1	BLUE VEIN 2	113.8	3.319	1760	51.33
Resplit:					
R/S 1	BLUE VEIN 2	130.3	3.800	1800	52.49
Standard:					
STD-M		1.38	0.040		
Mp-1a				69.7	2.03

Frank J. Pezzotti
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724



Doug Reddi
445-6497
445-6412
Vern & Gary

CERTIFICATE OF ASSAY AK 97- 978

ARNOLD SAVJORD
RR#5, SITE3, COMP11
KAMLOOPS, B.C.
V2C 6C2

12-Sep-97

ATTENTION: ARNOLD SAVJORD

Post-It™ Fax Note	7671E	Date	Sept	# of pages	1
To	Arnold	From			
Co./Dept.		Co.			
Phone #		Phone #			
Fax #		Fax #			

No. of samples received: 2
Sample type: Sand
PROJECT #: Not given
SHIPMENT #: Not given
Samples submitted by: Arnold Savjord

*10kg sample - run through Greenwood Mill (Roberts Mill)
Grade of concentrate + tailings 14:1 concentration*

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Pb (%)	Zn (%)
1	KAMI-CON	957.00	27.909	3220	93.91	3.03	0.71
2	KAMI-TAIL	24.20	0.706	126	3.65	0.11	0.04

QC DATA:

Resplit:
1 KAMI-CON 963.00 28.084 3150 91.86 3.14 0.73

Repeat:
1 KAMI-CON 952.00 27.763 3.09 0.72

Standard:
STD-M 1.65 0.048
CCU-1a 0.364 2.86

[Signature]
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

8-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 97-1114

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: ARNOLD SAVJORD

STREAM SAMPLES

No. of samples received: 4
Sample type: Stream
PROJECT #: None Given
SHIPMENT #: None Given
Samples submitted by: Arnold Savjord


Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	BAN - 1	0.8	1.17	5	50	<5	0.51	<1	7	3	8	2.47	<10	0.44	1418	4	0.02	7	1090	76	<5	<20	37	0.02	<10	26	<10	5	107
2	BAN - 2	0.8	1.61	10	60	<5	0.88	<1	6	2	4	2.28	10	0.32	2476	1	0.03	10	1120	32	<5	<20	82	0.02	<10	23	<10	12	149
3	BAN - 3	2.8	2.56	15	70	<5	0.93	<1	6	3	3	2.24	<10	0.35	1710	1	0.02	10	720	112	<5	<20	107	0.01	<10	25	<10	3	92
4	BAN - 4	>30	2.77	30	75	<5	0.51	<1	8	8	7	3.29	20	0.42	1935	2	0.02	8	1520	128	<5	<20	89	0.02	<10	32	<10	34	217

QC DATA:

Repeat:		Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	BAN - 1	0.8	1.19	10	45	<5	0.48	<1	6	1	6	2.32	<10	0.42	1389	4	0.02	6	1010	74	<5	<20	37	0.02	<10	24	<10	5	97
Standard:		Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
GEO'97		1.0	1.70	55	145	<5	1.89	<1	19	64	77	3.93	<10	0.98	672	<1	0.03	24	640	20	<5	<20	58	0.11	<10	75	<10	5	70

df/1093
XLS/97
fax: 573-1724

per

ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

10/29/97 10:30

250 573 4557

ECO-TECH KAM.

001



Attn - Mike Cathro

**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ANALYSIS AK 97- 1059

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

28-Oct-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 15
Sample type: Soil
PROJECT #: Not Given
SHIPMENT #: Not Given
Samples submitted by: Arnold Savjord

Post-it Fax Note 7671E		Date <i>Oct 29</i>	# of pages <i>1</i>
To		From	
Co./Dept.		Co.	
Phone #		Phone #	
Fax #		Fax #	


SOIL SAMPLE

ET #.	Tag #	Au (ppb)
15	15	140

QC DATA:

Standard:
GEO'97 125

XLS/97
fax: 573-1724

per 
ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 E.C. Certified Assayer

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 97-1059

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: ARNOLD SAVJORD

No. of samples received: 15
Sample type: Soil
PROJECT #: None Given
SHIPMENT #: None Given
Samples submitted by: Arnold Savjord

SOIL SAMPLES

Values in ppm unless otherwise reported

Et #	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	01	3.2	3.31	60	80	<5	0.47	<1	10	4	10	3.31	<10	0.23	671	2	0.03	4	450	46	<5	<20	54	0.01	<10	25	<10	8	131
2	02	0.8	2.15	5	45	<5	0.17	1	5	4	5	2.20	<10	0.19	187	<1	0.04	3	440	18	<5	<20	19	0.05	<10	30	<10	<1	62
3	03	1.2	1.98	10	40	<5	0.08	<1	4	3	5	2.02	<10	0.15	194	<1	0.03	4	350	18	<5	<20	9	0.05	<10	29	<10	<1	62
4	04	0.4	2.05	10	50	5	0.14	<1	6	5	5	2.10	<10	0.34	290	1	0.02	3	430	16	<5	<20	17	0.01	<10	27	<10	2	52
5	05	0.6	4.08	15	70	<5	0.37	<1	6	6	5	2.99	<10	0.26	217	2	0.02	5	750	20	<5	<20	37	0.03	<10	33	<10	5	75
6	06	1.2	2.89	5	65	<5	0.23	<1	6	6	5	2.80	<10	0.26	313	1	0.03	3	540	18	<5	<20	31	0.03	<10	34	<10	14	46
7	07	0.4	1.36	5	35	<5	0.17	<1	5	3	2	1.97	<10	0.25	344	<1	0.02	1	400	10	<5	<20	10	0.03	<10	29	<10	4	38
8	08	1.6	2.64	10	60	<5	0.19	<1	6	5	4	2.09	10	0.32	404	<1	0.03	3	790	18	<5	<20	22	0.02	<10	28	<10	11	43
9	09	0.4	2.06	5	65	<5	0.23	<1	6	3	3	2.11	<10	0.34	416	1	0.03	3	600	14	<5	<20	30	0.02	<10	26	20	4	51
10	10	<0.2	1.25	<5	20	<5	0.13	<1	6	3	2	1.71	<10	0.18	298	<1	0.01	1	530	8	<5	<20	12	0.02	<10	24	<10	3	26
11	11	0.4	2.46	5	55	5	0.10	<1	6	8	4	2.47	<10	0.22	169	<1	0.02	2	340	16	<5	<20	14	0.04	<10	35	<10	8	32
12	12	0.4	1.42	<5	40	5	0.17	<1	4	4	3	1.91	<10	0.20	208	<1	0.02	2	370	10	<5	<20	20	0.03	<10	25	<10	10	28
13	13	0.4	1.60	<5	65	5	0.21	<1	6	12	7	2.35	<10	0.34	358	<1	0.02	5	440	12	<5	<20	27	0.04	<10	36	<10	13	39
14	14	0.6	2.50	5	75	<5	0.08	<1	6	4	5	2.73	<10	0.41	449	2	0.03	4	530	18	<5	<20	10	<0.01	<10	30	<10	<1	64
15	15	29.6	2.40	580	60	10	0.24	<1	13	6	10	8.90	<10	0.15	550	8	0.03	2	1060	116	<5	<20	28	0.02	<10	48	<10	15	245


ARNOLD SAVJORD

ICP CERTIFICATE OF ANALYSIS AK 97-1059

ECO-TECH LABORATORIES LTD.

Et #.	Tag #	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	v	w	Y	Zn
QC DATA:																													
Repeat:																													
1	01	2.8	3.26	60	75	<5	0.50	<1	10	4	9	3.25	<10	0.24	672	2	0.01	4	450	44	<5	<20	55	0.01	<10	24	<10	7	125
10	10	0.2	1.22	10	20	<5	0.13	<1	6	3	2	1.69	<10	0.18	282	<1	0.01	1	540	10	<5	<20	11	0.02	<10	23	<10	3	27
Standard:																													
GEO'97		1.4	1.66	55	155	<5	1.66	<1	18	53	80	3.87	<10	0.92	658	<1	0.03	23	650	20	<5	<20	56	0.10	<10	72	<10	4	68

df/1059
XLS/97
fax: 573-1724



Frank J. Pezzotti
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97-403

ARNOLD SAVJORD
RR#5, SITE 3, COMP 112
KAMLOOPS, BC
V2C 6C2

3-Jun-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 2
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: ARNOLD

rocks - main trench.

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	KAMI A	59.80	1.744	2180.0	63.58
2	KAMI B	1.46	0.043	125.6	3.66

QC/DATA:

Resplit:

1	KAMI A	61.10	1.782	2220.0	64.74
---	--------	-------	-------	--------	-------

Repeat:

1	KAMI A	58.40	1.703	2225.0	64.89
---	--------	-------	-------	--------	-------

Standard:

STD-M	1.35	0.039	-	-
MPIa	-	-	70.0	2.04


ECO-TECH LABORATORIES LTD.

Frank J. Pezzotti, A.Sc.T.

B.C. Certified Assayer

XLS/97
fax: 573-1724

TENURES 359939-42


SLOCAN M.D.

VERNON M.D.
SLOCAN M.D.

Strutell

LOCATOR'S SKETCH STAMP	
(SUB) RECORDER'S INFORMATION	
CLAIM NAMES:	KAMI 8-FH
RECORD NUMBERS:	359939-942
MINING DIVISION:	SLOCAN
MAP NUMBER:	82E/16W
FEDERAL TITLES BRANCH DRAFTING INFORMATION	
DATE COMPLETED:	
INITIALS:	

82E/16W
0392832
82E/16W




Banting

TENURES 359937-38
SLOCAN M.D.

VERNON M.D.
SLOCAN M.D.

Strutell

LOCATOR'S SKETCH STAMP (SUB) RECORDER'S INFORMATION	
CLAIM NAMES:	KAMI 6-7
RECORD NUMBERS:	359937-938
MINING DIVISION:	SLOCAN
MAP NUMBER:	82L/1W & 82E/16E
MILWAUKEE BRANCH DRAFTING INFORMATION	
DATE COMPLETED:	
INITIALS:	



82L/1W
0392832
82E/16E

IP 680309 M
IP 680307 M

BANTING I

KAMI 6 KAMI 7 350956 233350 56X4W (233350)

IP 680309 M
IP 680307 M
257151 16506

BANTING I
350956 56X4W

Banting

BRITISH COLUMBIA
PROSPECTORS ASSISTANCE PROGRAM
PROSPECTING REPORT FORM (continued)

B. TECHNICAL REPORT

- One technical report to be completed for each project area.
- Refer to Program Requirements/Regulations, section 15, 16 and 17.
- If work was performed on claims a copy of the applicable assessment report may be submitted in lieu of the supporting data (see section 16) required with this TECHNICAL REPORT.

Name A. SAUTJORD Reference Number 97/98 - P75

LOCATION/COMMODITIES

Project Area (as listed in Part A) SLOCAN-KAMI 5 MINFILE No. if applicable _____

Location of Project Area NTS 82 E 16 W Lat _____ Long _____

Description of Location and Access By Highway 6 from HUMBLY to summit of Monashee - south on Rte 101 to the Valley Road - 1/2 mile to Rio Logging road - then 25 K on R10 to end of Road

Main Commodities Searched For GOLD - SILVER

Known Mineral Occurrences in Project Area _____

WORK PERFORMED

1. Conventional Prospecting (area) General
2. Geological Mapping (hectares/scale) _____
3. Geochemical (type and no. of samples) _____
4. Geophysical (type and line km) Soil sampling - 1000 along fault zone
5. Physical Work (type and amount) Stream sampling 20' above fault zone
6. Drilling (no., holes, size, depth in m, total m) _____
7. Other (specify) Drill, Blast remove waste - 300 Ton

SIGNIFICANT RESULTS

Commodities GOLD SILVER Claim Name KAMI 5

Location (show on map) Lat _____ Long _____ Elevation 5500

Best assay/sample type 4 03 - GOLD - 46 03 SILVER

Description of mineralization, host rocks, anomalies see report - MIKE CATMO

Supporting data must be submitted with this TECHNICAL REPORT
Information on this form is confidential for one year from the date of receipt subject to the provisions of the Freedom of Information Act.


SEE MAP 82F.008

KAMI 5



When Mr Cathro visited the property in October he took samples as per assays K1, K2, K3. The K1 sample was a chip sample from the newly exposed vein as per the attached picture & The K2 sample was a chip sample from the well rock.

The K3 sample was taken across the creek and approx 300 feet downstream from the exposed ore body. It was a grab sample of sulphide rock from the old diggings by the original prospector in the early part of the century. The sample was badly oxidized but the mineralization warrants further prospecting in the spring.



30-Oct-97

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

CERTIFICATE OF ANALYSIS AK97-1223

ATTENTION: ARNOLD SAVJORD

No. of samples received: 3
Sample type: Rock
PROJECT #: Kami 5 Property
SHIPMENT #: Not Given
Samples submitted by: M. Cathro

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	As Hg(ppb)	Sb	Te	Se
1	K1	730	504	33	*	*
2	K2		74	0.3		
3	K3		350	0.8		

QC DATA:


Resplit:
R/S 1 K1 730 529 38

Repeat:
1 K1 730 571 32

Standard:
GEO'97 1.4 59 3

NOTE *= Results to follow

XLS/97
fax: 573-1724

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97- 1223

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

29-Oct-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 3
Sample type: Rock
PROJECT #: Kami 5 Property
SHIPMENT #: Not Given
Samples submitted by: M. Cathro

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)	Cd (%)	Pb (%)	Zn (%)
1	K1	39.59	1.155	1000.0	29.16	0.164	5.08	7.60
<i>Walt</i> 2	K2	1.01	0.029	-	-	-	-	-
3	K3	0.83	0.024	52.4	1.53	-	-	-

QC/DATA:

Repeat:

2	K2	0.94	0.027	-	-	-	-	-
---	----	------	-------	---	---	---	---	---

Resplit:

R/S 1	K1	-	-	-	-	-	5.08	7.60
-------	----	---	---	---	---	---	------	------

Standard:

STD-M	1.60	0.047	-	-	-	-	-	-
CPb-I	-	-	-	-	-	-	-	4.42
MP-1a	-	-	69.7	2.03	-	-	4.33	19.02
CZN-1	-	-	-	-	-	0.134	-	-

NOTE: * = Metallic Screen Assay -Au

[Signature]
ECO-TECH LABORATORIES LTD.

per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724

4-Nov-97

ICP CERTIFICATE OF ANALYSIS AK 97- 1223

ARNOLD SAVJORD
RP#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

TOTAL DIGESTION

ATTENTION: ARNOLD SAVJORD

No. of samples received: 3
Sample type: ROCK
PROJECT #: KAMI 5 PROPERTY
SHIPMENT #: NONE GIVEN
Samples submitted by: MIKE CATHRO


ECO-TECH LABORATORIES LTD.
41 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

Phone: 604-573-5700
Fax: 604-573-4557

Values in ppm unless otherwise reported

Tag #	Ag	Al %	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	K %	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sr	Ti %	V	W	Y	Zn
K1	>30	0.73	200	15	1.35	>1000	31	167	650	>10	0.27	0.03	1349	<1	0.02	10	<10	>10000	117	0.02	6	<10	<1	>10000
K2	14.4	9.34	600	20	3.24	7	7	134	<1	2.44	3.23	0.68	990	3	0.09	3	810	328	202	0.15	10	<10	13	343
K3	>30	0.84	150	10	0.09	<1	9	259	<1	4.48	0.29	0.05	84	7	0.02	7	20	382	57	0.02	6	20	4	106
DATA:																								
split:																								
1 K1	>30	0.63	185	<5	1.16	>1000	28	150	619	>10	0.25	0.63	1108	<1	0.02	10	<10	>10000	111	0.02	5	<10	<1	>10000
peat:																								
1 K1	>30	0.70	190	5	1.24	>1000	29	161	608	>10	0.27	0.03	1295	<1	0.02	6	<10	>10000	109	0.02	5	<10	<1	>10000
standard:																								
SD-2	0.5	4.40	425	35	2.50	8	18	105	35	5.00	1.2	1.80	890	10	0.09	49	1140	68	370	0.49	101	<10	40	240
SD-3	0.4	3.76	1335	20	2.26	1	15	72	32	4.80	1.4	1.40	2845	6	0.82	26	1350	46	230	0.39	140	<10	38	209
SD-4	0.3	3.40	1815	10	2.60	7	12	90	50	4.34	1.2	1.20	1557	<1	1.40	24	800	20	320	0.42	111	<10	28	100

1223
S/97
x: 573-1724

per 
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

Assays attached were from grab samples - sulphide ore "as veins were exposed. Assay #1 was from a narrow vein - approx 6 by 3 feet. There are a number of small veins. The large vein No 5 was not exposed until late in October, shortly before the snow arrived. It appears to have the potential for a bulk sample. The assay #5 was a sulphide rich grab sample. The first requirement in the spring will be to remove the overburden and test the new vein for possible bulk sampling. Also, the assay on No 6 indicated that the ore body continues for a considerable distance and removing the overburden along strike will clarify this.



Outcrop of vein approx
30 metres up from main vein

DMT 31 129 NNNN 20" 03




Cleaning up after blasting
Note overburden.

-----"TZ NNNN 631 T2 LMO



Lower end of wire

---"21 NNNN 621 12 LMO



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97-1057

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

29-Sep-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 4
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: Arnold Savjord

Post-it Fax Note	7671E	Date	Sep 30	# of pages	3
To	Arnold	From			
Co./Dept.		Co.			
Phone #		Phone #			
Fax #		Fax #			

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	BAN COMP	54.60	1.592	1380	40.25
2	BAN NEW	19.10	0.557	1020	29.75
3	BAN FOOT	0.78	0.005	22.6	0.68
4	BAN TOP	0.26	0.008	15.4	0.45

1
2
3
4

QC/DATA:

Resplit:


1	BAN COMP	55.10	1.607	1390	40.54
---	----------	-------	-------	------	-------

Repeat:

1	BAN COMP	55.80	1.627	1390	40.54
---	----------	-------	-------	------	-------

Standard:

STD-M		1.49	0.043		
-------	--	------	-------	--	--


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724



ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING

10041 E. Trans Canada Hwy., R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-5700
Fax (250) 573-4557

CERTIFICATE OF ASSAY AK 97-1166

9-Oct-97

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

5

ATTENTION: ARNOLD SAVJORD

No. of samples received: 1
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: SAVJORD

ET #	Tag#	Au (g/t)	Au (oz/t)	Ag (g/t)	Ag (oz/t)
1	BLUE VEIN 2	139.4	4036	1630	47.54

5

QC/ DATA

Repeat	BLUE VEIN 2	113.8	3.319	1760	51.33
Result	R/S 1 BLUE VEIN 2	130.3	3.800	1800	52.49
Standard:					
STD-M		1.38	0040		
Mp-la				69.7	203

[Signature]
ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724

CERTIFICATE OF ASSAY AK 97-1158

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

7-00197

ATTENTION: ARNOLD SAVJORD

No. of samples received: 1
Sample type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: ARNOLD

ET #.	Tag #	Au (g/t)	Au (oz/t)	Ag* (g/t)	Ag* (oz/t)
1	NEW VEIN	5.62	0.193		




QC/DATA:

Repeat:
1 NEW VEIN 6.78 0.198

Resplit:
1 NEW VEIN 7.22 0.311


Standard:
STD-M 1.88 0.040

NOTE: * = Results to follow


per 
ECO-TECH LABORATORIES LTD
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

XLS/97
fax: 573-1724

In addition to trenching & stripping the main ore body, I also soil sampled & stream sampled. The soil samples #1-15 were at 50' intervals from the exposed ore along the fault (Banting Creek) in a northerly direction. No 15 sample provided non-positive info. and one of my first projects in 98 will be to set up a grid in the area of the #15 sample. The stream sample was limited to the area where the quartz vein appears to cut across the fault. I will be doing additional soil sampling on the other side of the creek next year.



3" = 500 M.



3" = 500 M.

30-Sep-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICF CERTIFICATE OF ANALYSIS AK 97-1059

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

Phone: 604-573-5700
Fax : 604-573-4557

SOIL SAMPLES

ATTENTION: ARNOLD SAVJORD

No. of samples received: 15
Sample type: Soil
PROJECT #: None Given
SHIPMENT #: None Given
Samples submitted by: Arnold Savjord

Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mo%	Mn	Mo	Na%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	01	3.2	3.31	60	80	<5	0.47	<1	10	4	10	3.31	<10	0.23	671	2	0.03	4	450	46	<5	<20	54	0.01	<10	25	<10	8	131
2	02	0.8	2.15	5	45	<5	0.17	1	5	4	5	2.20	<10	0.19	187	<1	0.04	3	440	18	<5	<20	19	0.05	<10	30	<10	<1	62
3	03	1.2	1.98	10	40	<5	0.08	<1	4	3	5	2.02	<10	0.15	194	<1	0.03	4	350	18	<5	<20	9	0.05	<10	29	<10	<1	62
4	04	0.4	2.05	10	50	5	0.14	<1	6	5	5	2.10	<10	0.34	290	1	0.02	3	430	16	<5	<20	17	0.01	<10	27	<10	2	52
5	05	0.6	4.08	15	70	<5	0.37	<1	6	6	5	2.99	<10	0.26	217	2	0.02	5	750	20	<5	<20	37	0.03	<10	33	<10	5	75
6	06	1.2	2.89	5	65	<5	0.23	<1	6	6	6	2.50	<10	0.26	313	1	0.03	3	540	18	<5	<20	31	0.03	<10	34	<10	14	46
7	07	0.4	1.56	5	35	<5	0.17	<1	5	6	2	1.97	<10	0.29	344	<1	0.82	1	400	10	<5	<20	18	0.03	<10	26	<10	4	35
8	08	1.6	2.64	10	60	<5	0.19	<1	6	5	4	2.09	10	0.32	404	<1	0.03	3	790	18	<5	<20	22	0.02	<10	28	<10	11	43
9	09	0.4	2.06	5	65	<5	0.23	<1	8	3	3	2.11	<10	0.34	416	1	0.03	3	600	14	<5	<20	30	0.02	<10	26	20	4	51
10	10	<0.2	1.25	<5	20	<5	0.13	<1	8	3	2	1.71	<10	0.18	288	<1	0.01	1	530	8	<5	<20	12	0.02	<10	24	<10	3	26
11	11	0.4	2.46	5	55	5	0.10	<1	6	8	4	2.47	<10	0.82	169	<1	0.02	2	340	16	<5	<20	14	0.04	<10	35	<10	8	32
12	12	0.4	1.42	<5	40	5	0.17	<1	4	4	3	1.91	<10	0.20	208	<1	0.02	2	370	16	<5	<20	20	0.03	<10	25	<10	10	28
13	13	0.4	1.60	<5	65	5	0.21	<1	6	12	7	2.35	<10	0.34	358	<1	0.02	5	440	12	<5	<20	27	0.04	<10	36	<10	13	39
14	14	0.6	2.50	5	75	<5	0.08	<1	6	4	5	2.73	<10	0.41	449	2	0.03	4	530	18	<5	<20	10	<0.01	<10	30	<10	<1	64
15	15	29.6	2.40	580	60	10	0.24	<1	13	6	10	8.90	<10	0.15	650	8	0.03	2	1060	116	<5	<20	28	0.02	<10	48	<10	15	245

10/29/97 10:30

250 573 4557

ECO-TECH KAM.

001



Attn - Mike Cathro

**ASSAYING
GEOCHEMISTRY
ANALYTICAL CHEMISTRY
ENVIRONMENTAL TESTING**

10041 E. Trans Canada Hwy, R.R. #2, Kamloops, B.C. V2C 6T4 Phone (250) 573-6700
Fax (250) 573-4557

CERTIFICATE OF ANALYSIS *AK 97-1059*

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

28-Oct-97

ATTENTION: ARNOLD SAVJORD

No. of samples received: 15
Sample type: Soil
PROJECT #: Not Given
SHIPMENT #: Not Given
Samples submitted by: *Arnold Savjord*

Post-It™ Fax Note	7671E	Date	<i>Oct 29</i>	# of pages	<i>1</i>
To		From			
Co./Dept.		Co.			
Phone #		Phone #			
Fax #		Fax #			

SOIL SAMPLE


<u>ET #.</u>	<u>Tag #</u>	<u>Au (ppb)</u>
<i>15</i>	<i>15</i>	<i>140</i>

QC DATA:

Standard:
GEO'97

125

XLS/97
fax: 573-1724

per 
ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

8-Oct-97

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK 97-1114

ARNOLD SAVJORD
RR#5, SITE 4, COMP 17
KAMLOOPS, BC
V2C 6C2

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: ARNOLD SAVJORD

STREAM SAMPLES

No. of samples received: 4

Sample type: Stream

PROJECT #: None Given

SHIPMENT #: None Given

Samples submitted by: Arnold Savjord


Values in ppm unless otherwise reported

Et #.	Tag #	Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Nb%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	BAN-1	0.8	1.17	5	50	<5	0.51	<1	7	3	8	2.47	<10	0.44	1418	4	0.02	7	1090	76	<5	<20	37	0.02	<10	26	<10	5	107
2	BAN-2	0.8	1.61	10	60	<5	0.86	<1	6	2	4	2.28	10	0.32	2476	1	0.03	10	1120	32	<5	<20	82	0.02	<10	23	<10	12	149
3	BAN-3	2.8	2.56	15	70	<5	0.93	<1	6	3	3	2.24	<10	0.35	1710	1	0.02	10	720	112	<5	<20	107	0.01	<10	25	<10	3	92
4	BAN-4	>30	2.77	30	75	<5	0.51	<1	8	8	7	3.29	20	0.42	1935	2	0.02	8	1520	128	<5	<20	89	0.02	<10	32	<10	34	217

QC DATA:

Repeat:		Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Nb%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
1	BAN-1	0.8	1.19	10	45	<5	0.48	<1	6	1	6	2.32	<10	0.42	1389	4	0.02	6	1010	74	<5	<20	37	0.02	<10	24	<10	5	97
Standard:		Ag	Al%	As	Ba	Bi	Ca%	Cd	Co	Cr	Cu	Fe%	La	Mg%	Mn	Mo	Nb%	Ni	P	Pb	Sb	Sn	Sr	Ti%	U	V	W	Y	Zn
	GEO'97	1.0	1.70	55	145	<5	1.89	<1	19	64	77	3.93	<10	0.98	672	<1	0.03	24	640	20	<5	<20	58	0.11	<10	75	<10	5	70

df/1093
XLS/97
fax: 573-1724


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer



OMT 31 129 NNNN 34"-----

Oct 15/97



Revised

Winter arriving early
approx. Oct 15/97

-----"32 NNNN 6ZT TS LMO



Looking down from working
area to camp - Sept 197
Access Road (K10) at bottom
of picture



97 19 2

Container for storing ore.
Holds 10 000 lbs Eliminates
loss of high grade & fines -
Can be dumped directly into
Dump truck or trailer.